

Larrondo LOTU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4)4 71 13 00
Fax:34-(4) 4 53 16 36



Management System
Approved
CERT.N°
SGI 6000360

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		126219		Date - Datum - Fecha				18 - 09 - 2012															
Our order N° Werks - Nr N° de Referencia		460027		Heat Schmelze Colada		337758		Your order N° Bestell - Nr Pedido N°		OL 4692																	
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde		BS 970:PART 3:1991.													
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 25,65 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		4		Bars Stäbe Barras		174		Weight Gewicht Peso		2432 Kg									
Requirements - Anforderungen - Exigencias																											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-11a. ASTM A 479 / A 479M-11. ASTM A 276-10. ASME SA 479 / SA 479M-11a. NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653F-02. 316S31AV-1.4404-1.4401-TP.316L-TP.316. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG								Anhang I Bsatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC																			
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico																					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA																					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kersbschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min.		325		375		550		20																	
		Max.																									
Temperature °C 20		Spec. N°. Probe Nr. Pro N°.		1		387		441		588		45		73		179											
C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co							
Min.										16,50		2,00		11,00													
Max.		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70									
		0,019		0,37		1,83		0,031		0,026		17,10		2,07		11,05		0,33		0,0210		0,10					
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional				O.K.				Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad				O.K.				Antimixing test Spektrale Verwechslungspr Antimezcla				O.K.				Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones																											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK																											
F11083 1/2" BSPP Cone Seat Swivel x Swivel Adaptor 10K																											
<div style="border: 2px solid red; padding: 5px; text-align: center;"> FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL </div>																											
EDV / EDP Acc. EN 10.204 Alfredo Molina Certification - Mng. Works Inspector Der Werkssachverständige Inspector de fábrica																											