

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SC1 6000360
ISO 14001 / SC1 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		192779		Date - Datum - Fecha		19 - 05 - 2014					
Our order N° Werks - Nr N° de Referencia		537068		Heat Schmelze Colada		371260		Your order N° Bestell - Nr Pedido N°		OL6135					
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.			
Shape and Size - Gegenstad Perfil y dimensión				Tolerance - Toleranz Tolerancia				Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso			
HEXAGON 19,05 mm				h 11 /DIN 176				4		306		2328 Kg			
Requirements - Anforderungen - Exigencias															
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC									
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertempe-Cold drawn/Gezogen/Estirado-															
Test results - Ergebnis der Prüfungen - Resultados de los ensayos															
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules						
RD. 10,00 mm.		Min.	325	375	550	20									
		Max.													
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	484	573	651	36	39	74	212						
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co				
Min.						16,50	2,00	11,00							
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70						
	0,015	0,39	1,76	0,033	0,027	17,00	2,03	11,00	0,37	0,0250	0,12				
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr Antimezcler			Grain Size Korngröße Tamaño de grano						
O.K.			O.K.			O.K.									
Remarks - Bemerkungen - Observaciones															
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.						
F11131 9/16" JIC SWIV FEM X 1/4" BSPP MALE ADAPTOR 15K 316L									Works Inspector Der Werkssachverständiger Inspector de fábrica						