Larrondo LOIU (VIZCAYA) España P.O. Box 1.323/48080 Bilbao Tel. 34-(4) 4 71 13 00 Fax.34-(4) 4 53 16 36

OLARRA U.K. LTD.



ACEROS INOXIDABLES

OIARRA

Trade Mark - Zeichen des Lieferwerkes Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger Sello del Inspector

indiger 3

FOREST PARK - CLEOBURY MORTIMER NR KIDDERMINSTER - DY 149BD - ENGLAND

· · · · · · · · · · · · · · · · · · ·			•		<u> </u>		·	······································	
Certificate type - APZ Nach Certificado tipo	Certificate nº - Prüf-Nr Certificado nº 138862				Date - Datum - Fecha 21 - 01 - 2013				
Our order N° Werks - Nr 501803 N°de Referencia	Heat Schmelze Colada	262659	Your order N Bestell - Nr Pedido Nº		L5398				
Steel Grade Werkstoff X-2-CRNIMO Calidad)-17-12-2 /	1.4404 MECA	MAX	According Entsprech Correspor	end EN	1 10	.272-2007.		
Shape and Size - Gegens Perfil y dimension HEXAGON 12.7 mg	Tolerance - Toleranz Tolerancia h11 /DIN 176 /EN 10278			Bundles Bunde Bultos	3	Bars Stäbe Barras	Weight Gewitcht Peso	1320 Kg	

Requirements - Anforderungen - Exigencias

EN 10.088-3.2005.

ASTM A 479 / A 479M-11.

ASTM A 276-10.

ASME SA 479 / SA 479M-11a.

SAE AMS 5653F-02.

NACE MR-0175-2003/ISO 15156-3 2009.

1.4401-TP.316L-TP.316.

PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG

Anhang I Bsatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC

Melting process / Erschmelzungsart / Proceso de Fusión

Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA

E.A.F. / A.O.D.

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

				,						, , ,	os de los ensa			
Dimension of Specimen Abmessungendes Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA	Rm N/mm MPA	2 %L 5	%L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules				
RD. 10,00 mm. Min.		200		235	235 500									
	·	•	Max.	1	-		900				315			
Temperature C Spec. No. Probe Nr. Pro No.		1	580		740 775		33		65	235				
errore, and discould the control		,	***************************************						į					
	С	Si	N	In	P	, ;	3	Cr	Мо	Ni	N	Co		_
Min.					**************************************			16,50	2,00	10,00]
Max.	0,030	1,00	2,	00	0,0	45 0,0	30	18,50	2,50	13,00	0,1000			
	0,019	0,519	1,	55	0,0	33 0,0	27	16,94	2,05	10,09	0,0540	0,268		
Besid	Visual and dimensional inspection Besichtingung und Ausmessung O.K. Control visual y dimensional			Rad	lioactivity ir lioaktivitäts strolde Radio	O.K.	Antimixing test Spektrosk Verwechslungspr O.K. Antimezcla			Grain Size Korngröss Tamaño d	0			

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

F11301
7/16" JIC Male x Male Adaptor 10K

EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.

Works Inspector

Der Werkssachverständige
Inspector de fäbrica