


Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador

Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		254350		Date - Datum - Fecha 09 - 12 - 2015																			
Our order N° Werks - Nr N° de Referencia		584938		Heat Schmelze Colada		399014		Your order N° Bestell - Nr Pedido N°				OL6922															
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde		BS 970:PART 3:1991.													
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 34,93 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		6		Bars Stäbe Barras		132		Weight Gewicht Peso		3454 Kg									
Requirements - Anforderungen - Exigencias												Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC															
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-14. ASTM A 276-15. ASME SA 479 / SA 479M-13 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG																											
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico																					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA																					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kerschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min. 325		375		550		20																			
Temperature °C 20		Spec. N° Probe Nr. Pro N°		1		360		402		557		47		50		73		174									
C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co							
Min.										18,50		2,00		11,00													
Max		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70									
		0,029		0,42		1,62		0,035		0,027		17,25		2,04		11,05		0,39		0,0300 0,18							
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional				O.K.				Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad				O.K.				Antimixing test Spektroskopische Verwechslungspr Antimezcla				O.K.				Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones																											
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK																											
F11533 1/2" BSP 'P' FIXED FEMALE GAUGE ADAPTOR X 1/2" NPT MALE 6K																											
EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica																											