

Larrundo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax 34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

OLARRA U.K. LTD.  
FOREST PARK - CLEOBURY MORTIMER  
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		228450		Date - Datum - Fecha 13 - 04 - 2015			
Our order N° Werks - Nr N° de Referencia		554804		Heat Schmelze Colada		390260		Your order N° Bestell - Nr Pedido N°			
								OL6556			
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde			
								BS 970:PART 3:1991.			
Shape and Size - Gegenstand Perfil y dimensión			Tolerance - Toleranz Tolerancia			Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso	
HEXAGON 22,23 mm			h 11 / DIN 176			8		475		4941 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Paraq.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min.	325	375	550	20					
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	439	573	646	36	39	74	212		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,021	0,41	1,79	0,034	0,028	17,05	2,02	11,00	0,57	0,0260	0,20
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						<b>FLOW TECHNOLOGY LTD</b> <b>TEST CERTIFICATE</b> <b>VERIFIED TRUE</b> <b>COPY OF ORIGINAL</b>			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.		
F11584 1/2" NPT HEX PLUG 10K 316L									Works Inspector Der Werkssachverständige Inspector de fábrica		