

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
**LRQA**  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo	<b>EN 10204/3.1</b>	Certificate n° - Prüf-Nr Certificado n°	<b>282156</b>	Date - Datum - Fecha	<b>26 - 07 - 2016</b>
---	---------------------	--	---------------	----------------------	-----------------------

Our order N° Werks - Nr N° de Referencia	<b>606534</b>	Heat Schmelze Colada	<b>414763</b>	Your order N° Bestell - Nr Pedido N°	<b>OL7352</b>
--	---------------	----------------------------	---------------	--	---------------

Steel Grade Werkstoff Calidad	<b>316-S-11 AV</b>	According to Entsprechend Corresponde	<b>BS 970:PART 3:1991.</b>
-------------------------------------	--------------------	---	----------------------------

Shape and Size - Gegenstad Perfil y dimensión <b>HEXAGON 34,93 mm</b>	Tolerance - Toleranz Tolerancia <b>h 11 /DIN 176</b>	Bundles Bunde Bultos	<b>6</b>	Bars Stäbe Barras	<b>138</b>	Weight Gewicht Peso	<b>3586 Kg</b>
---	--	----------------------------	----------	-------------------------	------------	---------------------------	----------------

Requirements - Anforderungen - Exigencias	
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU	Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC

Melting process / Erschmelzungsart / Proceso de Fusión	<b>E.A.F. / A.O.D.</b>	Heat treatment / Wärmebehandlung / Tratamiento térmico	<b>1060C 4H/Std WATER/WASSER/AGUA</b>
--	------------------------	--	---------------------------------------

**Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-**

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.	Min.	325	375	550	20				
	Max.								
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	379	416	574	44	47	72	174

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,025	0,45	1,72	0,034	0,027	17,00	2,02	11,00	0,36	0,0205	0,21

Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	<b>O.K.</b>	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	<b>O.K.</b>	Antimixing test Spektrosk Verwechslungspr Antimezcla	<b>O.K.</b>	Grain Size Korngröße Tamaño de grano
--	-------------	---	-------------	--	-------------	--

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.14. OK  
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK

**FLOW TECHNOLOGY LTD**  
**TEST CERTIFICATE**  
**VERIFIED TRUE**  
**COPY OF ORIGINAL**

F11731  
3/8" MP MALE X 3/8" NPT FEMALE ADAPTOR 15K 316L

EDV / EDP  
Acc. EN 10.204  
Marian Tejedo  
Quality Mng.

Works Inspector  
Der Werkssachverständige  
Inspector de fábrica