

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
**LRQA**  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo <b>EN 10204/3.1</b>		Certificate n° - Prüf-Nr Certificado n° <b>284867</b>		Date - Datum - Fecha <b>16 - 09 - 2016</b>							
Our order N° Werks - Nr <b>606526</b> N° de Referencia	Heat Schmelze <b>414375</b> Colada	Your order N° Bestell - Nr <b>OL7352</b> Pedido N°									
Steel Grade Werkstoff <b>316-S-11 AV</b> Calidad	According to Entsprechend <b>BS 970:PART 3:1991.</b> Corresponde										
Shape and Size - Gegenstand Perfil y dimensión <b>HEXAGON 22,23 mm</b>	Tolerance - Toleranz Tolerancia <b>h 11 / DIN 176</b>	Bundles Bunde <b>4</b> Bultos	Bars Stäbe <b>231</b> Barras	Weight Gewicht <b>2492 Kg</b> Peso							
Requirements - Anforderungen - Exigencias											
EN 10.088-3:2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>		Heat treatment / Wärmebehandlung / Tratamiento térmico <b>1060C 4H/Std WATER/WASSER/AGUA</b>									
<b>Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-</b>											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.	Min. 325	375	550	20							
	Max.										
Temperature °C <b>20</b>	Spec. N°. Probe Nr. Pro N°.	<b>1</b>	497	568	639	38	41	73	217		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,027	0,31	1,78	0,036	0,029	17,15	2,04	11,10	0,39	0,0250	0,22
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	<b>O.K.</b>		Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad		<b>O.K.</b>		Antimixing test Spektroskop Verwechslungspr Antimezcla		<b>O.K.</b>		Grain Size Korngrösse Tamaño de grano
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK			<b>FLOW TECHNOLOGY LTD</b> <b>TEST CERTIFICATE</b> <b>VERIFIED TRUE</b> <b>COPY OF ORIGINAL</b>						EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng.		
F11792 1/2" NPT x 3/4" JIC Male x Male Adaptor 10K									Works Inspector Der Werkssachverständige Inspector de fábrica		