


Larrendo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilibao
 Tel. 34-(4) 4 71 13 00
 Fax. 34-(4) 4 53 16 36


Management Systems
 Certified by
 LRQA
 ISO 9001 / SGI 6000366
 ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MCRTIMER
NRKIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador 

Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector 

Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 197510		Date - Datum - Fecha 19 - 06 - 2014							
Our order N° Werks - Nr 540735 N° de Referencia		Heat Schmelze 372813 Colada		Your order N° Bestell - Nr OL6213 Pedido N°							
Steel Grade Werkstoff 316-S-11 AV Calidad			According to Entsprechend BS 970:PART 3:1991. Corresponde								
Shape and Size - Gegenstand Perfil y dimensión ROUND 36 mm		Tolerance - Toleranz Tolerancia h 10 / ISO 286-1		Bundles Bunde 2 Bultos	Bars Stäbe Barras						
				Weight Gewicht Peso 940 Kg							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE.MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erhitzungsart / Proceso de Fusión E.A.F. / A.O.D.			Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA								
Solution annealed/Abgeschreckt/Hilf temple-Turned/Drehen/Torneado-Polished/Poliert/Pulido-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kernschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 190	225	490	40						
Temperature °C 20		Spec. N° Probe Nr. Pro N° 1	278	318	580	52	55	72	156		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,019	0,38	1,71	0,035	0,028	17,00	2,08	11,10	0,38	0,0235	0,16
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad			Anticorrosion test Spektralanalyse O.K. Antimezcla			Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK 100% US test/US prüfung. OK				FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL				EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica			
F11796 1/2" BSPP All Swivel Tee 20K											