


Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax. 34-(4) 4 53 16 36


Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 

Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		281065		Date - Datum - Fecha 15 - 07 - 2016			
Our order N° Werks - Nr N° de Referencia		602774		Heat Schmelze Colada		415794		Your order N° Bestell - Nr Pedido N°			
Steel Grade Werkstoff Calidad		316-S-11. AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.					
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 19,05 mm		Tolerance - Toleranz Tolerancia h 11 /DIN 176		Bundles Bunde 2 Bultos		Bars Stäbe 159 Barras		Weight Gewicht 1212 Kg Peso			
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-6175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG					Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.					Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA						
Solution annealed/Abgeschreckt/Hilf temple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	457	549	633	38	41	73	207		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,018	0,41	1,68	0,035	0,027	17,00	2,01	11,10	0,35	0,0280	0,21
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK											
F11908 9/16" JIC TUBE NUT 10K 316L - HEX TUBE NUT											
EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica											