

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		279702		Date - Datum - Fecha		06 - 07 - 2016					
Our order N° Werks - Nr N° de Referencia		596389		Heat Schmelze Colada		411298		Your order N° Bestell - Nr Pedido N°		OL7136					
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.			
Shape and Size - Gegenstand Perfil y dimensión				Tolerance - Toleranz Tolerancia				Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso			
HEXAGON 22,23 mm				h 11 /DIN 176				2		92		973 Kg			
Requirements - Anforderungen - Exigencias															
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC									
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-															
Test results - Ergebnis der Prüfungen - Resultados de los ensayos															
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kernschlag / Resiliencia ISO V Jules						
RD. 10,00 mm.		Min.	325	375	550	20									
		Max.													
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	513	598	657	34	37	72	217						
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co				
Min.						16,50	2,00	11,00							
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70						
	0,022	0,38	1,65	0,033	0,028	16,95	2,01	11,10	0,47	0,0295	0,17				
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezclia			Grain Size Korngröße Tamaño de grano						
O.K.			O.K.			O.K.									
Remarks - Bemerkungen - Observaciones															
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK															
F11925 1/4" BSPP Fixed Female x 1/4" NPT Male Hex Adaptor 10K															
EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.  Works Inspector Der Werkssachverständige Inspector de fábrica															