



Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax. 34-(4) 4 53 16 36

Management Systems  
Certified by  
**LRQA**  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador 

Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector 

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Certificate type - APZ Nach Certificado tipo <b>EN 10204/3.1</b>		Certificate n° - Prüf-Nr Certificado n° <b>309228</b>		Date - Datum - Fecha <b>10 - 04 - 2017</b>							
Our order N° Werks - Nr <b>617567</b> N° de Referencia		Heat Schmelze <b>430983</b> Colada		Your order N° Bestell - Nr <b>0L7534</b> Pedido N°							
Steel Grade Werkstoff <b>316-S-11 AV</b> Calidad			According to Entsprechend <b>BS 970:PART 3:1991.</b> Corresponde								
Shape and Size - Gegenstad Perfil y dimensión <b>HEXAGON 25,65 mm</b>		Tolerance - Toleranz Tolerancia <b>h 11 /DIN 176</b>		Bundles Bunde <b>2</b> Bultos	Bars Stäbe <b>76</b> Barras						
				Weight Gewicht <b>1059 Kg</b> Peso							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-15. ASTM A 276/A 276M-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. 316S31AV-1.4404-1.4401-Type 316-Type 316L.			PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>			Heat treatment / Wärmebehandlung / Tratamiento térmico <b>1060C 4H/Std WATER/WASSER/AGUA</b>								
<b>Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-</b>											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	407	494	602	44	47	73	187		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,022	0,65	1,60	0,038	0,025	17,10	2,02	11,00	0,44	0,0245	0,33
Visual and dimensional inspection Besichtigung und Ausmessung <b>O.K.</b> Control visual y dimensional		Radioactivity inspection Radioaktivitätskontrolle <b>O.K.</b> Control de Radioactividad		Antimixing test Spektrosk Verwechslungspr <b>O.K.</b> Antimezcla		Grain Size Korngröße Tamaño de grano					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						<b>FLOW TECHNOLOGY LTD</b> <b>TEST CERTIFICATE</b> <b>VERIFIED TRUE</b> <b>COPY OF ORIGINAL</b>				EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.	
F12143 1/4" NPT Hex Full Couplings 10K										Works Inspector Der Werkssachverständige Inspector de fábrica	

369527  
369528