

Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax.34-(4) 4 53 16 36


Management Systems
 Certified by
 LRQA
 ISO 9001 / SGI 6000360
 ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY.14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		278465		Date - Datum - Fecha 24 - 06 - 2016			
Our order N° Werks - Nr N° de Referencia		602779		Heat Schmelze Colada		411918		Your order N° Bestell - Nr Pedido N°			
								OL7282			
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde		BS 970:PART 3:1991.	
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 25,65 mm			Tolerance - Toleranz Tolerancia h 11 /DIN 176			Bundles Bunde Bultos		4		Bars Stäbe Barras	
								146		Weight Gewicht Peso	
										2018 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-15. ASME SA 479 / SA 479M-15 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG					Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.				Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA							
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	414	497	612	42	45	71	187		
C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co	
Min.					16,50	2,00	11,00				
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,020	0,50	1,78	0,040	0,028	17,10	2,01	11,10	0,43	0,0250 0,17	
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional		Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad		Antimixing test Spektralk Verwechslungspr Antimezcla		Grain Size Korngröße Tamaño de grano					
		O.K.		O.K.		O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E. 14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK					FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL					EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica	
F12310 1/4" BSPP Gauge x 1/4" NPT Hex Socket 10K											