

Larrondo LOIU (VIZCAYA) España  
 P O Box 1 323/48080 Bilbao  
 Tel. 34-(4) 4 71 13 00  
 Fax 34-(4) 4 53 16 36

Management Systems  
 Certified by  
 LRQA  
 ISO 9001 / SGI 6000368  
 ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD

TEST CERTIFICATE  
 VERIFIED TRUE  
 COPY OF ORIGINAL

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.  
 FOREST PARK - CLEOBURY MORTIMER  
 NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes  
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		229307		Date - Datum - Fecha		20 - 04 - 2015	
Our order N° Werks - Nr N° de Referencia		557512		Heat Schmelze Colada		390260		Your order N° Bestell - Nr Pedido N°		OL6598	
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.					
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 23,37 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos		2	
								Bars Stäbe Barras		80	
								Weight Gewicht Peso		917 Kg	
Requirements - Anforderungen - Exigencias						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG											
Melting process / Erschmelzungsart / Proceso de Fusión				Heat treatment / Wärmebehandlung / Tratamiento térmico							
E.A.F. / A.O.D.				1060C 4H/Std WATER/WASSER/AGUA							
Solution annealed/Abgeschreckt/Hipertempe-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	Z %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min.	325	375	550	20					
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	423	516	638	41	44	72	197		