

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48086 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax 34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1970678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo <b>EN 10204/3.1</b>		Certificate n° - Prüf-Nr Certificado n° <b>296951</b>		Date - Datum - Fecha <b>23 - 12 - 2016</b>							
Our order N° Werks - Nr <b>617568</b> N° de Referencia		Heat Schmelze <b>424796</b> Colada		Your order N° Bestell - Nr <b>0L7534</b> Pedido N°							
Steel Grade Werkstoff <b>316-S-11 AV</b> Calidad			According to Entsprechend <b>BS 970:PART 3:1991.</b> Corresponde								
Shape and Size - Gegenstand Perfil y dimensión <b>HEXAGON 27,94 mm</b>		Tolerance - Toleranz Tolerancia <b>h 11 /DIN 176</b>		Bundles Bunde <b>4</b> Bultos	Bars Stäbe <b>152</b> Barras						
				Weight Gewicht <b>2586 Kg</b> Peso							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-15. ASTM A 276/A 276M-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103-12/ISO 17945-2015. 316S31AV-1.4404-1.4401-Type 316-Type 316L.			PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>			Heat treatment / Wärmebehandlung / Tratamiento térmico <b>1060C 4H/Std WATER/WASSER/AGUA</b>								
<b>Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-</b>											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	428	520	640	40	43	72	197		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,018	0,48	1,54	0,039	0,027	17,10	2,01	11,05	0,42	0,0255	0,21
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional <b>O.K.</b>		Radioactivity inspection Radioaktivitätskontrolle <b>O.K.</b> Control de Radioactividad		Antimixing test Spektroskop Verwechslungspr <b>O.K.</b> Antimezcla		Grain Size Korngröße Tamaño de grano					
Remarks - Bemerkungen - Observaciones										EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.  Works Inspector Der Werkssachverständige Inspector de fábrica	
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK  F12632 1/2" BSPP C/S M/M ADAPTOR 10K 316L											