

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD

TEST CERTIFICATE  
VERIFIED TRUE  
COPY OF ORIGINAL

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.  
FOREST PARK - CLEOBURY MORTIMER  
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		312521		Date - Datum - Fecha 12 - 05 - 2017			
Our order N° Werks - Nr N° de Referencia		631305		Heat Schmelze Colada		430975		Your order N° Bestell - Nr Pedido N°			
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 38,1 mm		Tolerance - Toleranz Tolerancia h 11 /DIN 176		Bundles Bunde Bultos		4		Bars Stäbe Barras			
						65		Weight Gewicht Peso			
								1986 Kg			
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-15. ASTM A 276/A 276M-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. NORSOK M-630 and MDS S01.					316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag. 4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>					Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA						
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A - %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
		Max.									
Temperature °C 20	Spec. N°. Probe Nr. Pro N°	1	443	530	645	39	42	72	202		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,020	0,57	1,61	0,036	0,029	17,15	2,02	11,00	0,46	0,0250	0,33
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional		O.K.		Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad		O.K.		Antimixing test Spektrosk Verwechslungspr Antimezcla		O.K.	
										Grain Size Korngröße Tamaño de grano	
										5-6 ASTM E-112-13	
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK											
F12740 1/2" NPT Hex Cap 10K											
EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.  Works Inspector Der Werkssachverständige Inspector de fábrica											