

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

**OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		318565		Date - Datum - Fecha		27 - 06 - 2017					
Our order N° Werks - Nr N° de Referencia		638053		Heat Schmelze Colada		434431		Your order N° Bestell - Nr Pedido N°		OL7884					
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.			
Shape and Size - Gegenstand Perfil y dimensión				Tolerance - Toleranz Tolerancia				Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso			
HEXAGON 28,58 mm				h 11 /DIN 176				4		124		2119 Kg			
Requirements - Anforderungen - Exigencias															
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-15. ASTM A 276/A 276M-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. NORSOK M-630 and MDS S01.						316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC									
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-															
Test results - Ergebnis der Prüfungen - Resultados de los ensayos															
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2%	Rp 1%	Rm	A	A _L	Z	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules						
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%								
Min.		325	375	550	20										
Max.															
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	402	489	590	45	48	74	183						
>															
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co				
Min.						16,50	2,00	11,00							
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70						
	0,018	0,59	1,63	0,034	0,026	17,15	2,00	11,00	0,35	0,0190	0,14				
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano						
O.K.			O.K.			O.K.			5-6 ASTM E-112-13						
Remarks - Bemerkungen - Observaciones										EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica					
IC test acc./IK prüfung nach ASTM A 262 E.15, OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK															
F12898 3/4" NPT Hex Plug 15K															