



Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger 
Sello del Inspector

| | | | | | |
|---|---------------------|--|---------------|----------------------|-----------------------|
| Certificate type - APZ Nach Certificado tipo | EN 10204/3.1 | Certificate n° - Prüf-Nr Certificado n° | 279646 | Date - Datum - Fecha | 05 - 07 - 2016 |
|---|---------------------|--|---------------|----------------------|-----------------------|

| | | | | | |
|--|---------------|----------------------------|---------------|--|---------------|
| Our order N° Werks - Nr N° de Referencia | 601380 | Heat Schmelze Colada | 411918 | Your order N° Bestell - Nr Pedido N° | OL7225 |
|--|---------------|----------------------------|---------------|--|---------------|

| | | | |
|-------------------------------------|--------------------|---|----------------------------|
| Steel Grade Werkstoff Calidad | 316-S-11 AV | According to Entsprechend Corresponde | BS 970:PART 3:1991. |
|-------------------------------------|--------------------|---|----------------------------|

| | | | | | | | | | |
|---|-------------------------|------------------------------------|----------------------|----------------------------|----------|-------------------------|------------|---------------------------|----------------|
| Shape and Size - Gegenstand Perfil y dimensión | HEXAGON 22,23 mm | Tolerance - Toleranz Tolerancia | h 11 /DIN 176 | Bundles Bunde Bultos | 4 | Bars Stäbe Barras | 200 | Weight Gewicht Peso | 2103 Kg |
|---|-------------------------|------------------------------------|----------------------|----------------------------|----------|-------------------------|------------|---------------------------|----------------|

Requirements - Anforderungen - Exigencias

| | |
|---|---|
| EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG | Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC |
|---|---|

| | | | |
|--|------------------------|--|---------------------------------------|
| Melting process / Erschmelzungsart / Proceso de Fusión | E.A.F. / A.O.D. | Heat treatment / Wärmebehandlung / Tratamiento térmico | 1060C 4H/Std WATER/WASSER/AGUA |
|--|------------------------|--|---------------------------------------|

Solution annealed/Abgeschreckt/Hipertempie-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

| Dimension of Specimen Abmessungen des Probestabes Medida de las probetas | Rp0,2% N/mm2 MPA | Rp 1% N/mm2 MPA | Rm N/mm2 MPA | A %L 5D | A %L 4D | Z % | Hardness Härte HBw | Impact test / Kerschschlag / Resiliencia ISO V Jules | |
|--|---------------------------------|-----------------------|--------------------|------------|------------|--------|--------------------------|---|-----|
| RD. 10,00 mm. | Min. | 325 | 375 | 550 | 20 | | | | |
| | Max. | | | | | | | | |
| Temperature °C 20 | Spec. N° Probe Nr. Pro N° | 1 | 480 | 576 | 645 | 36 | 39 | 74 | 212 |

| | C | Si | Mn | P | S | Cr | Mo | -Ni | Cu | N | Co |
|------|-------|------|------|-------|-------|-------|------|-------|------|--------|------|
| Min. | | | | | | 16,50 | 2,00 | 11,00 | | | |
| Max. | 0,030 | 1,00 | 2,00 | 0,045 | 0,030 | 18,50 | 2,50 | 14,00 | 0,70 | | |
| | 0,020 | 0,50 | 1,78 | 0,040 | 0,028 | 17,10 | 2,01 | 11,10 | 0,43 | 0,0250 | 0,17 |

| | | | | | | | |
|--|-------------|---|-------------|--|-------------|--|--|
| Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional | O.K. | Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad | O.K. | Antimixing test Spektroskop Verwechslungspr Antimezcla | O.K. | Grain Size Korngröße Tamaño de grano | |
|--|-------------|---|-------------|--|-------------|--|--|

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.14. OK
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK

F13068
1/4" BSP P FIXED FEMALE X 1/4" NPT MALE ADAPTOR 10K 316L

EDV / EDP
Acc. EN 10.204
Marian Tejado
Quality Mng.

Works Inspector
Der Werkssachverständige
Inspector de fábrica