



Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax. 34-(4) 4 53 16 36

Management Systems
 Certified by
 LRQA
 ISO 9001 / SGI 6000360
 ISO 14001 / SGI 1870670

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador 
 Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector 

Certificate type - APZ Nach
 Certificado tipo **EN 10204/3.1** Certificate n° - Prüf-Nr
 Certificado n° **196049** Date - Datum - Fecha
10 - 06 - 2014

Our order N°
 Werks - Nr **548580** Heat
 Schmelze **374462** Your order N°
 N° de Referencia Bestell - Nr **OL6404**
 Pedido N°

Steel Grade
 Werkstoff **316-S-11 AV** According to
 Entsprechend **BS 970:PART 3:1991.**
 Calidad Corresponde

Shape and Size - Gegenstand
 Perfil y dimensión **HEXAGON 25,65 mm** Tolerance - Toleranz
 Tolerancia **h 11 / DIN 176** Bundles
 Bunde **10** Bars
 Stäbe **351** Weight
 Gewicht **4972 Kg**
 Bultos Barras Peso

Requirements - Anforderungen - Exigencias
EN 10.088-3.2005. Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC
EN 10.272-2007.
ASTM A 182 / A 182M-13a.
ASTM A 479 / A 479M-13b.
ASTM A 276-13a.
ASME SA 479 / SA 479M-13
NACE MR-0175-2003/ISO 15156-3 2009.
SAE AMS 5653H-12.
316S31AV-1.4404-1.4401-Type 316-Type 316L.
PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG

Melting process / Erschmelzungsart / Proceso de Fusión
E.A.F. / A.O.D. Heat treatment / Wärmebehandlung / Tratamiento térmico
1060C 4H/Std WATER/WASSER/AGUA

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

| Dimension of Specimen Abmessungen des Probestabes Medida de las probetas | Rp0.2% N/mm2 MPA | Rp 1% N/mm2 MPA | Rm N/mm2 MPA | A %L 5D | A [*] %L 4D | Z % | Hardness Härte HBw | Impact test / Kerschlag / Resiliencia ISO V Jules | |
|--|---------------------------------|-----------------------|--------------------|------------|-------------------------|--------|--------------------------|--|-----|
| RD. 10,00 mm. | Min. | 325 | 375 | 550 | 20 | | | | |
| | Max. | | | | | | | | |
| Temperature °C 20 | Spec. N° Probe Nr. Pro N° | 1 | 408 | 495 | 616 | 43 | 46 | 73 | 192 |

| | C | Si | Mn | P | S | Cr | Mo | Ni | Cu | N | Co |
|------|-------|------|------|-------|-------|-------|------|-------|------|--------|------|
| Min. | | | | | | 16,50 | 2,00 | 11,00 | | | |
| Max. | 0,030 | 1,00 | 2,00 | 0,045 | 0,030 | 18,50 | 2,50 | 14,00 | 0,70 | | |
| | 0,022 | 0,39 | 1,78 | 0,033 | 0,021 | 17,20 | 2,04 | 11,05 | 0,45 | 0,0355 | 0,19 |

Visual and dimensional inspection
 Besichtigung und Ausmessung **O.K.** Radioactivity inspection
 Radioaktivitätskontrolle **O.K.** Antimixing test
 Spektrosk Verwechslungspr **O.K.** Grain Size
 Korngröße
 Control visual y dimensional Control de Radioactividad Antimezcla Tamaño de grano

Remarks - Bemerkungen - Observaciones
IC test acc./IK prüfung nach ASTM A 262 E.02. OK
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK
F13228
1/4" NPT Female x 3/8" NPT Male Hex Adaptor 10K
EDV / EDP
Acc. EN 10.204
Alfredo Molina
Certification
Mng.
 Works Inspector
 Der Werkssachverständige
 Inspector de fábrica