

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 279646		Date - Datum - Fecha 05 - 07 - 2016							
Our order N° Werks - Nr N° de Referencia 601380	Heat Schmelze Colada 411918	Your order N° Bestell - Nr Pedido N° OL7225									
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde									
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 22,23 mm	Tolerance - Toleranz Tolerancia h 11 /DIN 176	Bundles Bunde 4 Bultos	Bars Stäbe 200 Barras	Weight Gewicht Peso 2103 Kg							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
FLOW TECHNOLOGY LTD			TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL								
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.		Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas RD. 10,00 mm.	Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A ₅ %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules			
Temperature °C 20	Spec. N° Probe Nr. Pro N° 1	480	576	645	36	39	74	212			
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,020	0,50	1,78	0,040	0,028	17,10	2,01	11,10	0,43	0,0250	0,17
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional O.K.	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad O.K.	Antimixing test Spektrosk Verwechslungspr Antimezcla O.K.	Grain Size Korngröße Tamaño de grano								
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK										EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica	
F13345 3/4" x 9/16" JIC Male x Male Adaptor 10K											