



Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		323048		Date - Datum - Fecha		08 - 09 - 2017	
Our order N° Werks - Nr N° de Referencia		640184		Heat Schmelze Colada		437814		Your order N° Bestell - Nr Pedido N°		OL7920	
Steel Grade Werkstoff Calidad						316-S-11 AV					
According to Entsprechend Corresponde						BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión ROUND 19,05 mm			Tolerance - Toleranz Tolerancia h 9 /DIN 671 /EN 10278			Bundles Bunde 6 Bultos		Bars Stäbe Barras		Weight Gewicht Peso 3576 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-15. ASME SA 479 / SA 479M-15 ASTM A 276/A 276M-16a. ASME SA 276-2015 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015.						316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.						Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-Polished/Poliert/Pulido-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
Temperature °C 20		Spec. N° Probe Nr. Pro N°	1	478	543	628	38	41	74	207	
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,018	0,68	1,63	0,033	0,028	17,15	2,01	11,05	0,36	0,0210	0,18
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.			5-6 ASTM E-112-13		
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.15. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica		
F13372 9/16" Medium Pressure Plug Extended c/w 3mm Hole											