


Larrondo LOIU (VIZCAYA) España
 P.O. Box 1.323/48080 Bilbao
 Tel. 34-(4) 4 71 13 00
 Fax. 34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
 Anagrama del suministrador

Works Inspector Stamp - Werkssachverständiger
 Sello del Inspector

Certificate type - APZ Nach **EN 10204/3.1** Certificate n° - Prüf-Nr **289738** Date - Datum - Fecha **26 - 10 - 2016**
 Certificado tipo Certificado n°

Our order N° **614326** Heat **417709** Your order N° **OL7475**
 Werks - Nr Schmelze Colada Bestell - Nr Pedido N°

Steel Grade **316-S-11 AV** According to **BS 970:PART 3:1991.**
 Werkstoff Entsprechend Correspondence
 Calidad

Shape and Size - Gegenstand **HEXAGON 27,94 mm** Tolerance - Toleranz **h 11 /DIN 176** Bundles **7** Bars **228** Weight **3919 Kg**
 Perfil y dimensión Tolerancia Bunde Stäbe Gewicht
 Bultos Barras Peso

Requirements - Anforderungen - Exigencias

EN 10.088-3.2014.	316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC
EN 10.272-2007.	
ASTM A 182 / A 182M-15.	
ASTM A 479 / A 479M-15.	
ASTM A 276-16a.	
ASME SA 479 / SA 479M-15	
SAE AMS 5653H-12.	
NACE MR-0175/ISO 15156-3 2009.	
NACE MR-0103-12/ISO 17945-2015.	
NORSOK M-630 and MDS S01.	

Melting process / Erschmelzungsart / Proceso de Fusión **E.A.F. / A.O.D.** Heat treatment / Wärmebehandlung / Tratamiento térmico **1060C 4H/Std WATER/WASSER/AGUA**

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A' %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.	Min.	325	375	550	20				
	Max.								
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	417	504	622	41	44	71	197

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,019	0,41	1,71	0,035	0,022	17,05	2,02	11,20	0,34	0,0250	0,17

Visual and dimensional inspection **O.K.** Radioactivity inspection **O.K.** Antimixing test **O.K.** Grain Size **O.K.**
 Besichtigung und Ausmessung Control de Radioactividad Antimezclia Spektroskop Verwechslungspr Korngrösse
 Control visual y dimensional Tamaño de grano

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.14. OK
 Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

F13385
 1/2" BSPP C/S X 1/4" NPT M/M RED ADAPTOR 10K 316L

EDV / EDP
 Acc. EN 10.204
 Marian Tejedo
 Quality Mng.
 Works inspector
 Der Werkssachverständige
 Inspector de fábrica