

Larrondo LORU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD

TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		275284		Date - Datum - Fecha		01 - 06 - 2016													
Our order N° Werks - Nr N° de Referencia		598357		Heat Schmelze Colada		412866		Your order N° Bestell - Nr Pedido N°		OL7177													
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.											
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 19,05 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		4		Bars Stäbe Barras		304		Weight Gewicht Peso		2351 Kg					
Requirements - Anforderungen - Exigencias												Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC											
<p>EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-15. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG</p>																							
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico																	
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA																	
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																							
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																							
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kerschschlag / Resiliencia ISO V Jules							
RD. 10,00 mm.		Min.		325		375		550		20													
		Max.																					
Temperature °C 20		Spec. N° Probe Nr. Pro N°.		1		491		579		648		34		37		72		217					
		C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co	
Min.												16,50		2,00		11,00							
Max.		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70					
		0,019		0,36		1,69		0,036		0,028		17,05		2,10		11,00		0,39		0,0210		0,22	
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional				Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad				O.K.				Antimixing test Spektrosk Verwechslungspr Antimezcla				O.K.				Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones																							
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK												EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.											
F13503 1/4" MEDIUM PRESSURE FEMALE X 1/8" NPT MALE 15K 316L												Works Inspector Der Werkssachverständige Inspector de fábrica											