

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD

TEST CERTIFICATE  
VERIFIED TRUE  
COPY OF ORIGINAL

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.  
FOREST PARK - CLEOBURY MORTIMER  
NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		262125		Date - Datum - Fecha		16 - 02 - 2016	
Our order N° Werks - Nr N° de Referencia		601396		Heat Schmelze Owlada		405944		Your order N° Bestell - Nr Pedido N°		OL7224	
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.					
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 28,58 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos		6	
								Bars Stäbe Barras		219	
								Weight Gewicht Peso		3809 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-15. ASME SA 479 / SA 479M-13 NACE MR-0175/ISO 15158-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión				Heat treatment / Wärmebehandlung / Tratamiento térmico							
E.A.F. / A.O.D.				1060C 4H/Std WATER/WASSER/AGUA							
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min.	325	375	550	20					
		Max.									
Temperature°C 20	Spec. N°. Probe Nr. Pro N°.	1	494	576	683	35	38	69	217		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,028	0,39	1,73	0,037	0,027	17,05	2,00	11,00	0,37	0,0275	0,23
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones										EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.	
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK										Works Inspector Der Werkssachverständige Inspector de fábrica	
F13885 1/4" BSPP FXD FEMALE GAUGE X 1/4" BSPP MALE 15K 316L											