



Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		347271		Date - Datum - Fecha 22 - 03 - 2018									
Our order N° Werks - Nr N° de Referencia		650469		Heat Schmelze Colada		452722		Your order N° Bestell - Nr Pedido N°				OL8212					
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 34,93 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde 5 Bultos		Bars Stäbe 96 Barras.		Weight Gewicht Peso		2506 Kg			
Requirements - Anforderungen - Exigencias												316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
EN 10.088-3.2014. EN 10.272-2016. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-17. ASTM A 276/A 276M-17. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. NORSOK M-630 and MDS S01.						Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.						Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																	
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																	
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules								
RD. 10,00 mm.		Min.	325	375	550	20											
		Max.															
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	397	485	591	45	48	73	183								
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co						
Min.						16,50	2,00	11,00									
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70								
	0,020	0,47	1,59	0,031	0,028	17,15	2,01	11,05	0,36	0,0200	0,20						
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano			5-6 ASTM E-112-13					
O.K.			O.K.			O.K.											
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica					
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK F13925 1/4" BSPP CS MALE X 1/2" BSPP FXD FEM ADAPTOR 10K 316L																	

We hereby certify that material described herein complies with the requirements agreed on the order.

Firmado digitalmente por / Signed digitally by:
ACEROS INOXIDABLES OLARRA SA - CIF A48663546
Fecha / Date:22-03-2018 10:27