

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		353660		Date - Datum - Fecha 17 - 05 - 2018					
Our order N° Werks - Nr N° de Referencia		660402		Heat Schmelze Cojada		455972		Your order N° Bestell - Nr Pedido N°					
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.							
Shape and Size - Gegenstad Perfil y dimensión		HEXAGON 52,07 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos	4	Bars Stäbe Barras	44	Weight Gewicht Peso	2483 Kg
Requirements - Anforderungen - Exigencias													
EN 10.088-3.2014. EN 10.272-2016. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-17. ASTM A 276/A 276M-17. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. NORSOK M-630 and MDS S01.						316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC							
Melting process / Erschmelzungsart / Proceso de Fusión				Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.				1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-													
Test results - Ergebnis der Prüfungen - Resultados de los ensayos													
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kersbschlag / Resiliencia				
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%	Härte HBw	ISO V Jules				
Min.		325	375	550	20								
Max.													
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	409	500	611	42	45	71	187				
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co		
Min.						16,50	2,00	11,00					
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70				
	0,016	0,50	1,59	0,032	0,028	17,15	2,02	11,05	0,31	0,0195	0,21		
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano				
O.K.			O.K.			O.K.			5-6 ASTM E-112-13				
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica	
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK F13977 M18 x 1.5 Metric Male x Male Adaptor 10K (10s)													

We hereby certify that material described herein complies with the requirements agreed on the order.