

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		292317		Date - Datum - Fecha		18 - 11 - 2016																	
Our order N° Werks - Nr N° de Referencia		614322		Heat Schmelze Colada		419457		Your order N° Bestell - Nr Pedido N°		OL7476																	
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.															
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 55 mm			Tolerance - Toleranz Tolerancia h 11 /DIN 176			Bundles Bunde Bultos		2		Bars Stäbe Barras		17		Weight Gewicht Peso		1111 Kg											
Requirements - Anforderungen - Exigencias												PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC															
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. NACE MR-0103-12/ISO 17945-2015. 316S31AV-1.4404-1.4401-Type 316-Type 316L.																											
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico																					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA																					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kersbschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min.		325		375		550		20																	
		Max.																									
Temperature °C 20		Spec. N°. Probe Nr. Pro N°.		1		416		501		622		42		45		73		197									
C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co							
Min.										16,50		2,00		11,00													
Max.		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70									
		0,018		0,57		1,53		0,033		0,029		17,10		2,02		11,05		0,37		0,0265 0,16							
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional				O.K.				Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad				O.K.				Antimixing test Spektrosk Verwechslungspr Antimezcla				O.K.				Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.															
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK												Works Inspector Der Werkssachverständige Inspector de fábrica															
F13996 M52 x 2 Metric Male x Male Adaptor 10K (42L)												362540, 362541															