

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36

Management Systems  
Certified by  
**LRQA**  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

**FLOW TECHNOLOGY LTD**

**TEST CERTIFICATE  
VERIFIED TRUE  
COPY OF ORIGINAL**

ACEROS INOXIDABLES

**OLARRA**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



**OLARRA U.K. LTD.  
FOREST PARK - CLEOBURY MORTIMER  
NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Certificate type - APZ Nach Certificado tipo	<b>EN 10204/3.1</b>	Certificate n° - Prüf-Nr Certificado n°	<b>275202</b>	Date - Datum - Fecha	<b>01 - 06 - 2016</b>
---	---------------------	--	---------------	----------------------	-----------------------

Our order N° Werks - Nr N° de Referencia	<b>601383</b>	Heat Schmelze Colada	<b>408963</b>	Your order N° Bestell - Nr Pedido N°	<b>OL7225</b>
--	---------------	----------------------------	---------------	--	---------------

Steel Grade Werkstoff Calidad	<b>316-S-11 AV</b>	According to Entsprechend Corresponde	<b>BS 970:PART 3:1991.</b>
-------------------------------------	--------------------	---	----------------------------

Shape and Size - Gegenstad Perfil y dimensión <b>HEXAGON 28,58 mm</b>	Tolerance - Toleranz Tolerancia <b>h 11 /DIN 176</b>	Bundles Bunde Bultos	<b>6</b>	Bars Stäbe Barras	<b>221</b>	Weight Gewicht Peso	<b>3853 Kg</b>
---	--	----------------------------	----------	-------------------------	------------	---------------------------	----------------

Requirements - Anforderungen - Exigencias

EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-15. ASME SA 479 / SA 479M-15 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG	<b>Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC</b>
--	--

Melting process / Erschmelzungsart / Proceso de Fusión	<b>E.A.F. / A.O.D.</b>	Heat treatment / Wärmebehandlung / Tratamiento térmico	<b>1060C 4H/Std WATER/WASSER/AGUA</b>
--	------------------------	--	---------------------------------------

**Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-**

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.	Min.	325	375	550	20				
	Max.								
Temperature °C 20	Spec. N°. Probe Nr. Pro N°.	1	408	507	630	42	45	71	192

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,022	0,42	1,74	0,033	0,026	17,05	2,20	11,00	0,37	0,0280	0,26

Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	<b>O.K.</b>	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	<b>O.K.</b>	Antimixing test Spektrsk Verwechslungspr Antimezcla	<b>O.K.</b>	Grain Size Korngröße Tamaño de grano
--	-------------	---	-------------	---	-------------	--

Remarks - Bemerkungen - Observaciones <b>IC test acc./IK prüfung nach ASTM A 262 E.14. OK</b> <b>Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK</b>  <b>F14043</b> <b>1 1/16" JIC HEX PLUG 10K 316L</b>	<b>EDV / EDP</b> <b>Acc. EN 10.204</b> <b>Marian Tejedo</b> <b>Quality Mng.</b>  Works Inspector Der Werkssachverständige Inspector de fábrica
---	---