



Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach **EN 10204/3.1** Certificate n° - Prüf-Nr **316113** Date - Datum - Fecha **06 - 06 - 2017**
Certificado tipo Certificado n°

Our order N° **623243** Heat **435438** Your order N° **OL7645**
Werks - Nr Schmelze Colada Bestell - Nr Pedido N°

Steel Grade **316-S-11 AV** According to **BS 970:PART 3:1991.**
Werkstoff Entsprechend Correspondence
Calidad

Shape and Size - Gegenstand **ROUND 25,4 mm** Tolerance - Toleranz **k 12 / ISO 286-1 /10060** Bundles **2** Bars **1136 Kg**
Perfil y dimensión Tolerancia Bunde Stäbe Gewicht
Bultos Barras Peso

Requirements - Anforderungen - Exigencias
EN 10.088-3.2014. **316S31AV-1.4404-1.4401-Type 316-Type 316L.**
EN 10.272-2007. **PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU**
Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC
ASTM A 182/A 182M-16.
ASTM A 479 / A 479M-15.
ASTM A 276/A 276M-16a.
ASME SA 479 / SA 479M-15
NORSOK M-630 and MDS S01.
SAE AMS 5653H-12.
NACE MR-0175/ISO 15156-3 2015.
NACE MR-0103/ISO 17945-2015.

Melting process / Erschmelzungsart / Proceso de Fusión **E.A.F. / A.O.D.** Heat treatment / Wärmebehandlung / Tratamiento térmico
1060C 4H/Std WATER/WASSER/AGUA

Solution annealed/Abgeschreckt/Hipertemple-Turned/Drehen/Torneado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules
RD. 10,00 mm.	Min.	190	225	490	40			
	Max.							
Temperature °C 20	Spec. N° 1	306	345	592	49	52	72	163
Spec. N° Probe Nr. Pro N°								

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,022	0,60	1,58	0,034	0,025	17,15	2,00	11,00	0,36	0,0185	0,14

Visual and dimensional inspection **O.K.** Radioactivity inspection **O.K.** Antimixing test **O.K.** Grain Size
Besichtigung und Ausmessung Control de Radioactividad Spektrosk Verwechslungspr Antimezcla Korngröße
Control visual y dimensional Tamaño de grano

Remarks - Bemerkungen - Observaciones
IC test acc./IK prüfung nach ASTM A 262 E.15. OK
F14071
1 1/16" JIC SWIV CAP 10K 316L
EDV / EDP
Acc. EN 10.204
Marian Tejedo
Quality Mng.
Works Inspector
Der Werkssachverständige
Inspector de fábrica

313153-
313144