

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		362619		Date - Datum - Fecha 10 - 09 - 2018											
Our order N° Werks - Nr N° de Referencia		660395		Heat Schmelze Colada		460899		Your order N° Bestell - Nr Pedido N°				OL8449							
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde				BS 970:PART 3:1991.			
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 31,75 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		5		Bars Stäbe Barras		121		Weight Gewicht Peso		2598 Kg	
Requirements - Anforderungen - Exigencias																			
EN 10.088-3.2014. EN 10.272-2016. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-17. ASTM A 276/A 276M-17. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015. NORSOK M-630 and MDS S01.						316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL							
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico													
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA													
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																			
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																			
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kersbschlag / Resiliencia										
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%	Härte HBw	ISO V Jules										
		Min.	325	375	550	20													
		Max.																	
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	377	416	576	44	47	72	174										
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co								
Min.						16,50	2,00	11,00											
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70										
	0,017	0,57	1,57	0,033	0,028	17,08	2,04	11,03	0,39	0,0270	0,12								
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrsk Verwechlungspr Antimezcla			Grain Size Korngrösse Tamaño de grano			5-6 ASTM E-112-13							
O.K.			O.K.			O.K.													
Remarks - Bemerkungen - Observaciones																			
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK												EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica							
F14518 1/2" NPT RT HEX PLUG 10K 316L																			
We hereby certify that material described herein complies with the requirements agreed on the order.																			