



CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a : **EN 10204 (2004) , 3.1 / ISO 10474 (2013) , 3.1**

Certificato nr. **MEST330711 / 2018 /**

Nach/According to/Selon

Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
VALBRUNA U.K. LTD.
OLDBURY ROAD
B70 9BH - WEST BROMWICH B70 9BH GB - GB

Stato di fornitura : **Hot rolled Degreased Annealed**
 Lieferzustand **COLD PROCESSED**
 Delivery state
 Etat de livraison

Produttore :
 Hersteller/Item/Usine productrice

ACCIAIERIE VALBRUNA S.P.A.

Ordine nr: **810056090 Sheffield**

Tipo di Elaborazione: **E+AOD**
 Erschmelzungsart
 Melting process
 Mode d'elaboration

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Bestell
 Your order
 Commande

Conferma ordine nr: **EI18010397**

Qualità: **1.4401/1.4404/316/316L**
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werksachverständigen
 Inspector's stamp/Poinçon de l'essayeur

MR

Avviso di Spedizione: **D-VI18030396**

Marca: **MVAPML (MAXIVAL)**
 Markenbezeichnung
 Brand / Nuance

Punzonatura: **1.4401/4/316/L**
 Kennzeichnung
 Marking
 Marquage

SPECIFICHE :

Note:

Anforderungen / Requirements / Exigences

Aufzeichnungen / Notes / Notes

VAL STOCK 2010 1.4404/316L A,CF
 AISI 316
 AISI 316L
 AMS 5648 M S31600 A
 AMS 5653 H S31603 A,CF
 ASME SA182 2017 S31600 A (0)
 ASME SA182 2017 S31603 A (1)
 ASME SA276 2017 S31600 A,CF (2)
 ASME SA276 2017 S31603 A,CF (3)
 ASME SA479 2017 S31600 A (4)
 ASME SA479 2017 S31603 A (5)
 ASTM A182 2018 S31600 A (6)
 ASTM A182 2018 S31603 (7)
 ASTM A262 2015 PRACTICE E
 ASTM A276 2017 S31600 A,CF
 ASTM A276 2017 S31603 A,CF
 ASTM A314 2015 S31600
 ASTM A314 2015 S31603
 ASTM A370 2017 .
 ASTM A479 2018 S31600 A
 ASTM A479 2018 S31603 A
 ASTM E10 2017 .
 ASTM E8 2016A .
 EN 10088-3 2014 1.4401 A,CF
 EN 10088-3 2014 1.4404 A,CF
 EN 10272 2007 1.4401 A,CF
 EN 10272 2007 1.4404 A,CF
 ISO 148-1 2016 .
 ISO 6506-1 2005 .
 ISO 6892-1 2016 .
 NACE MR0103 2015 S31600 A (8)
 NACE MR0103 2015 S31603 A (9)
 NACE MR0175 2015 S31600 A (A)
 NACE MR0175 2015 S31603 A (B)
 QQ-S-763 F 316 A,CF
 QQ-S-763 F 316L A,CF

- (0)Section II Part A 2017 EDITION For products machined directly from bar refer to ASME SA479.
- (1)Section II Part A 2017 EDITION For products machined directly from bar refer to ASME SA479.
- (2)Section II Part A 2017 EDITION
- (3)Section II Part A 2017 EDITION
- (4)Section II Part A 2017 EDITION
- (5)Section II Part A 2017 EDITION
- (6)For products machined directly from bar refer also to ASTM A479.
- (7)For products machined directly from bar refer also to ASTM A479.
- (8)ANSI/NACE MR0103/ISO 17945 November 23, 2015
- (9)ANSI/NACE MR0103/ISO 17945 November 23, 2015
- (A)ANSI/NACE MR0175/ISO 15156-3, third edition November 23,2015
- (B)ANSI/NACE MR0175/ISO 15156-3, third edition November 23,2015

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

Tolleranza: h11 - DIN668/EN10278

Tolleranza/Allowance/Tolerance

Pos. nr. Pos. nr. Item nr. Nr. de poste	Oggetto Gegenstand Product description Descrip. du produit	Dimensioni - mm Abmessungen Dimension Dimension	Lunghezza - mm Länge Length Longueur	Colata Schmelze Heat Coulée	Pezzi Stückzahl Pieces Pieces	Peso - KG Gewicht Weight Poids	Lotto nr. Losnr. Lot nr. Lot nr.
0011	Hexagon	32,000	3055/ 3070	275705	43	922,0	728307200

F14874
3/8" NPT FEM X 1/4" NPT MALE 10K 316L

Vicenza, 28/11/18

VCQ008 - MEST330711

(Mod. MCE2) WSP70C648FEACF94FASB72C135EA5EEEDB0

Il collaudatore di stabilimento / der Werkssachverständige / Works inspector / L'agent d'usine

M.RIZZOTTO

Pagina - 1 di 3



CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a : **EN 10204 (2004) , 3.1 / ISO 10474 (2013) , 3.1**

Certificato nr. **MEST330711 / 2018 /**

Nach/According to/Selon

Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
VALBRUNA U.K. LTD.
OLDBURY ROAD
B70 9BH - WEST BROMWICH B70 9BH GB - GB

Stato di fornitura : **Hot rolled Degreased Annealed COLD PROCESSED**
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore :
 Hersteller/Item/Usine productrice

Ordine nr: **810056090 Sheffield**
 Bestell
 Your order
 Commande

Tipo di Elaborazione: **E+AOD**
 Erschmelzungsart
 Melting process
 Mode d'elaboration

ACCIAIERIE VALBRUNA S.P.A.

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Conferma ordine nr: **EI18010397**
 Werks/Our Order/Ref nr.

Qualità: **1.4401/1.4404/316/316L**
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werksachverständigen
 Inspector's stamp/Poinçon de l'assesseur

MR

Avviso di Spedizione: **D-VI18030396**
 Lieferanzeige/Packing list/B.L.

Marca: **MVAPML (MAXIVAL)**
 Markenbezeichnung
 Brand / Nuance

Punzonatura: **1.4401/4/316/L**
 Kennzeichnung
 Marking
 Marquage

TEST ALLO STATO DI FORNITURA

Test on delivery condition Prüfung auf lieferbarem produkt test a l'etat de fourniture Prueba sobre el material así como entregado

1) L=longitudinale/längs, T=trasversale/quer, Q=Tangenziale/tangential

TEST	Provetta/ Probestab Specimen/Eprouvette Breite Diam. Spess. Width Diam. Thickness Larg. diam. epais mm	°C	Posiz. Saggio Probenlage Location Emplacement 1)	Snervamento		Resistenza	Allungamento		Strizione		Resilienza			Durezza	
				Streckgrenze Yield Stress Limite elastique Rp 0,2% N/mm2	Streckgrenze Yield Stress Limite elastique Rp 1% N/mm2	Zugfestigkeit Tensile strength Resistance à traction Rm N/mm2	Bruchdehnung Elongation Allongement A5 %	E 4d %	Einschnürung Reduction of area Striction Z %	RA %	Kerbschlagarbeit Impact Value Resilience KV J	186	186	186	186
Valori richiesti		min		207	235	517	20	30	-	50	100			140	
Anforderungen/Required values Valeurs demandées		max				900								235	
A	10	20	L	513	558	671	44	46	66	66	198	186	193	222	

TEST ALLO STATO DI FORNITURA

Test on delivery condition / Prüfung auf lieferbarem produkt / Test a l'etat de fourniture / Prueba sobre el material así como entregado

TEST	min	max
A Grain size for ASTM E112		5

Mechanical properties according to ASTM A370.

Brinnell hardness according to ASTM E10

Tensile testing according to ASTM E8

Impact testing according to ISO 148-1

Brinnell hardness according to ISO 6506-1

Tensile testing according to ISO 6892-1

Analisi chimica

Chemische Zusammensetzung/Chemical Analysis/Analyse chimique

Colata /Heat Schmelze/Coulée	min - max	-	1,25	16,50	2,00	-	10,00	-	-	-	-	-	-	-	-	-
	0,030	1,00	2,00	18,00	2,50	1,00	13,00	0,040	0,030	0,100	-	-	-	-	-	-
	C %	Si %	Mn %	Cr %	Mo %	Cu %	Ni %	P %	S %	N %						
275705	0,014	0,54	1,47	16,55	2,06	0,45	10,16	0,030	0,024	0,068						

Corrosion test in 16% sulfuric acid and copper sulfate solutions

Test standard: **ASTM A262-Practice E**

Test	Heat treatment before test	Length of Period (h)	Test temp (°C)	Bend Angle (°)	Ø spindle (mm)	Result of visual inspection at 20 x magnification after bend test	Result
Intergranular corrosion	Sensitization	15	boil	180	5	Absence of cracks	SATISFACTORY

F14874

3/8" NPT FEM X 1/4" NPT MALE 10K 316L

Vicenza, 28/11/18

VCQ008 - MEST330711

(Mod. MCE2) WSP70C648F9ACF94FASB72C135EA5EEEDB0

Il collaudatore di stabilimento / der Werkssachverständige / Works inspector / L'agent d'usine

M.RIZZOTTO

Pagina - 2 di 3



CERTIFICATO DI COLLAUDO - ABNAHMEPRUEFZEUGNIS - INSPECTION CERTIFICATE - CERTIFICAT DE RECEPTION

In conformità a : EN 10204 (2004) , 3.1 / ISO 10474 (2013) , 3.1

Certificato nr. MEST330711 / 2018 /

Nach/According to/Selon

Prüfung/Test/Essai

Cliente / Besteller/Purchaser/Client
 VALBRUNA U.K. LTD.
 OLDBURY ROAD
 B70 9BH - WEST BROMWICH B70 9BH GB - GB

Stato di fornitura : Hot rolled Degreased Annealed
 COLD PROCESSED
 Lieferzustand
 Delivery state
 Etat de livraison

Produttore :
 Hersteller/Item/Usine productrice

Ordine nr: 810056090 Sheffield

Bestell
 Your order
 Commande

Tipo di Elaborazione: E+AOD
 Erschmelzungsart
 Melting process
 Mode d'elaboration

ACCIAIERIE VALBRUNA S.P.A.

Marchi di Fabbrica:
 Zeichen des Lieferwerkes
 Trade marks
 Sigles de l'usine productrice



Conferma ordine nr: EI18010397

Werks/Our Order/Ref nr.

Qualità: 1.4401/1.4404/316/316L
 Werkstoff/Grade/Nuance

Punzone del Collaudatore:
 Stempel des Werkssachverständigen
 Inspector's stamp/Poinçon de l'assesseur

MR

Avviso di Spedizione: D-VI18030396

Lieferanzeige/Packing list/B.L.

Marca: MVAPML (MAXIVAL)
 Markenbezeichnung
 Brand / Nuance

Punzonatura: 1.4401/4/316/L
 Kennzeichnung
 Marking
 Marquage

Corrosion test in 16% sulfuric acid and copper sulfate solutions

Test standard: UNI EN ISO 3651-2 Method A

Test	Heat treatment before test	Length of Period (h)	Test temp (°C)	Bend Angle (°)	Ø spindle (mm)	Result of visual inspection at 20 x magnification after bend test	Result
Intergranular corrosion	Sensitized T1	20	boil	90	5	Absence of cracks	SATISFACTORY

Reduction ratio = 36,8 : 1

Material solution annealed 1080° C for 1h/water cooled.

Sono state soddisfatte tutte le condizioni richieste
 Die gestellten Anforderungen sind it. Anlage erfüllt
 The material has been furnished in accordance with the requirements
 Le materiel à été trouvé conforme aux exigences

Controllo antimescolanza: OK
 Verwechslungsprüfung: spectralanalytisch durchgeführt
 Antimixing testing performed: OK
 Contrôle antimélange fait: r.a.s.

Controllo visivo e dimensionale: soddisfa le esigenze
 Besichtigung und Ausmessung: ohne Beanstandung
 Visual inspection and dimensional checks:satisfactory
 Contrôle visuel et dimensions: satisfaisant

Melted and manufactured in Italy No welding or weld repair Material free from Mercury contamination

We declare that the finished product is checked for radioactive contamination through Portal System when it leaves the production plant.

QUALITY MANAGEMENT SYSTEM CERTIFIED BY LLOYD'S REGISTER ACCORDING TO ISO 9001 : 2015, IATF 16949 : 2016, AS 9100D

The Quality Management System is Certified acc. Pressure Equipment Directive "[97/23/EC]" Annex 1,s.,4.3 and 2014/68/EU by TUEV and LLOYD'S
 Any act of tampering, modification, alteration, counterfeiting and/or falsification and/or any other action which modifies the contents of this test certificate shall constitute a violation of applicable civil and criminal laws. Acciaierie Valbruna shall protect its rights and interests before any competent court, authority and jurisdiction.

Maxival and/or Valplus grades/products are manufactured with ladle techniques to control composition, distribution, size and shape of non-metallic inclusions for improved machinability.

The supplied product conforms to requirements expressly requested by the purchaser and conforms to requirements specified by certified norms and standards. Should the product be used for more severe, critical and/ or in any case different applications than those the material is generally intended for, any different and/or supplementary requirements shall be specifically demanded, at least, upon order of the Product by the Purchaser. Acciaierie Valbruna SpA shall not be responsible for any improper use of the Products.

F14874

3/8" NPT FEM X 1/4" NPT MALE 10K 316L

Vicenza, 28/11/18

VCQ008 - MEST330711

(Mod. MCE2) WSP70C648FEACF94FA5B72C135EA5EEEDB0

Il collaudatore di stabilimento / der Werkssachverständige / Works inspector / L'agent d'usine

M.RIZZOTTO

Pagina - 3 di 3