

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo	EN 10204/3.1	Certificate n° - Prüf-Nr Certificado n°	373882	Date - Datum - Fecha	03 - 01 - 2019
---	---------------------	--	---------------	----------------------	-----------------------

Our order N° Werks - Nr N° de Referencia	671604	Heat Schmelze Colada	469486	Your order N° Bestell - Nr Pedido N°	OL8686
--	---------------	----------------------------	---------------	--	---------------

Steel Grade Werkstoff Calidad	316-S-11 AV	According to Entsprechend Corresponde	BS 970:PART 3:1991.
-------------------------------------	--------------------	---	----------------------------

Shape and Size - Gegenstad Perfil y dimensión HEXAGON 19,05 mm	Tolerance - Toleranz Tolerancia h 11 /DIN 176	Bundles Bunde Bultos	4	Bars Stäbe Barras	351	Weight Gewicht Peso	2586 Kg
---	--	----------------------------	----------	-------------------------	------------	---------------------------	----------------

Requirements - Anforderungen - Exigencias	
EN 10.088-3.2014. EN 10.272-2016. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-17. ASTM A 276/A 276M-17. ASME SA 479 / SA 479M-15 ASME SA 182 / SA 182M-15 ASME SA 276-2015 NACE MR-0103/ISO 17945-2015. NACE MR-0175/ISO 15156-3 2015.	NORSOK M-630 and MDS S01. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L-F.316-F.316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC

Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.	Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA
--	---

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.	Min.	325	375	550	20					
	Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	467	543	636	40	43	74	197	195/199/194

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,019	0,63	1,63	0,030	0,028	17,16	2,05	11,01	0,39	0,0225	0,19

Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	O.K.	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	O.K.	Antimixing test Spektrsk Verwechlungspr Antimezcla	O.K.	Grain Size Korngrösse Tamaño de grano	5-6 ASTM E-112-13
--	-------------	---	-------------	--	-------------	---	--------------------------

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.15. OK
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK
No welding or weld repair.
Free from mercury or radio-activity contamination.

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

EDV / EDP
Acc. EN 10.204
Marian Tejado
Quality Mng.

Works Inspector
Der Werkssachverständige
Inspector de fábrica

F15097
3/8" MP FEMALE CAP 316L

We hereby certify that material described herein complies with the requirements agreed on the order.