


Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 149BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		193253		Date - Datum - Fecha		21 - 05 - 2014	
Our order N° Werks - Nr N° de Referencia		542651		Heat Schmelze Colada		372805		Your order N° Bestell - Nr Pedido N°		OL6278	
Steel Grade Werkstoff Calidad						316-S-11 AV					
According to Entsprechend Corresponde						BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión			Tolerance - Toleranz Tolerancia			Bundles Bunde Bultos		Bars Stäbe Barras		Weight Gewicht Peso	
HEXAGON 28,58 mm			h 11 / DIN 176			6		200		3442 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kernschlag / Resiliencia		
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%	Härte HBw	ISO V Jules		
		Min.	325	375	550	20					
		Max.									
Temperature °C	Spec. N° Probe Nr. Pro N°	1	397	442	588	43	46	72	179		
20											
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,020	0,44	1,66	0,035	0,028	16,95	2,05	11,10	0,40	0,0240	0,17
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskopische Verwechslungspr Antimixia			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						<b>FLOW TECHNOLOGY LTD</b> <b>TEST CERTIFICATE</b> <b>VERIFIED TRUE</b> <b>COPY OF ORIGINAL</b>			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.		
F10080 3/4" X 1/4" NPT HEX RED NIPPLE 15K 316L									Works Inspector Der Werksachverständige Inspector de fábrica		