

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36



Quality Management System  
Approved CERT. Nº  
SGI 6000360

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 149BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		135959		Date - Datum - Fecha 13 - 12 - 2012			
Our order N° Werks - Nr N° de Referencia		500395		Heat Schmelze Colada		343293		Your order N° Bestell - Nr Pedido N°			
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde							
				BS 970:PART 3:1991.							
Shape and Size - Gegenstand Perfil y dimensión ROUND 25,4 mm		Tolerance - Toleranz Tolerancia k 12 / ISO 286-1 / 10060		Bundles Bunde Bultos		1		Bars Stäbe Barras			
								Weight Gewicht Peso 1175 Kg			
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-11a. ASTM A 479 / A 479M-11. ASTM A 276-10. ASME SA 479 / SA 479M-11a. NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653F-02. 316S31AV-1.4404-1.4401-TP.316L-TP.316. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG					Anhang I Bsatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>				Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA							
Solution annealed/Abgeschreckt/Hilfper temple-Turned/Drehen/Torneado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 190	225	490	40						
		Max.									
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	346	394	618	47		72	179		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,024	0,32	1,79	0,032	0,027	17,25	2,06	11,00	0,39	0,0270	0,19
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK											
F10091 1/4" BSP Swivel Female x 1/4" BSP P Male 90° Elbow 10K											
EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.  Works Inspector Der Werkssachverständige Inspector de fábrica											

**FLOW TECHNOLOGY LTD**  
**TEST CERTIFICATE**  
**VERIFIED TRUE**  
**COPY OF ORIGINAL**