


Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax 34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		205713		Date - Datum - Fecha 26 - 09 - 2014					
Our order N° Werks - Nr N° de Referencia		550523		Heat Schmelze Colada		377531		Your order N° Bestell - Nr Pedido N°					
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.							
Shape and Size - Gegenstad Perfil y dimensión		HEXAGON 19,05 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos	2	Bars Stäbe Barras	167	Weight Gewicht Peso	1270 Kg
Requirements - Anforderungen - Exigencias													
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC							
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico							
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA							
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-													
Test results - Ergebnis der Prüfungen - Resultados de los ensayos													
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kerschschlag / Resiliencia				
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%	Härte HBw	ISO V Jules				
Min.		325	375	550	20								
Max.													
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	450	562	643	36	39	72	212				
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co		
Min.						16,50	2,00	11,00					
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70				
	0,026	0,49	1,73	0,033	0,028	17,00	2,05	11,05	0,39	0,0275	0,18		
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano				
O.K.			O.K.			O.K.							
Remarks - Bemerkungen - Observaciones													
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK										EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica			
F10136 1/4" BSP SWIV CAPS 15K 316L													
FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL													