

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 233946		Date - Datum - Fecha 25 - 05 - 2015							
Our order N° Werks - Nr 577500 N° de Referencia	Heat Schmelze 391565 Colada	Your order N° Bestell - Nr OL6804 Pedido N°									
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde									
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 34,93 mm	Tolerance - Toleranz Tolerancia h 11 /DIN 176	Bundles Bunde 10 Bultos	Bars Stäbe 222 Barras	Weight Gewicht 5792 Kg Peso							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.		Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.	Min. 325	375	550	20							
	Max.										
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	378	423	571	47	50	74	179		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min						16,50	2,00	11,00			
Max	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,030	0,42	1,87	0,034	0,029	17,00	2,01	11,00	0,37	0,0260	0,18
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	O.K.	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	O.K.	Antimixing test Spektrosk Verwechslungspr Antimezcla	O.K.	Grain Size Korngröße Tamaño de grano					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK F10690 3/4" Medium Pressure Female x 1/2" OD Twin Ferrule Comp 6K										EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica	

FLOW TECHNOLOGY LTD

TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL