

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax. 34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 600360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		198460		Date - Datum - Fecha 30 - 06 - 2014							
Our order N° Werks - Nr N° de Referencia		532121		Heat Schmelze Colada		371286		Your order N° Bestell - Nr Pedido N°							
								OL6010							
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde							
								BS 970:PART 3:1991.							
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 20,83 mm			Tolerance - Toleranz Tolerancia h 11 /DIN 176			Bundles Bunde Bultos		2		Bars Stäbe Barras		Weight Gewicht Peso		1008 Kg	
Requirements - Anforderungen - Exigencias															
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-13a. ASTM A 479 / A 479M-13b. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-TP.316L-TP.316. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG							Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico									
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA									
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-															
Test results - Ergebnis der Prüfungen - Resultados de los ensayos															
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules						
RD. 10,00 mm.		Min.	325	375	550	20									
		Max.													
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	612	680	703	32	35	65	212						
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co				
Min.						16,50	2,00	11,00							
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70						
	0,016	0,35	1,76	0,036	0,028	17,05	2,00	11,00	0,39	0,0290	0,14				
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano						
O.K.			O.K.			O.K.									
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica			
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK															
F10746 3/8" MEDIUM PRESSURE MALE X 3/4" JIC MALE ADAPTOR 15K															