

Larronde LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		219248		Date - Datum - Fecha		26 - 01 - 2015		
Our order N° Werks - Nr N° de Referencia		554789		Heat Schmelze Colada		381186		Your order N° Bestell - Nr Pedido N°		OL6555		
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.						
Shape and Size - Gegenstad Perfil y dimensión		HEXAGON 15,88 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos	2	Bars Stäbe Barras	Weight Gewicht Peso	1040 Kg
Requirements - Anforderungen - Exigencias												
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC						
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico						
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA						
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-												
Test results - Ergebnis der Prüfungen - Resultados de los ensayos												
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules			
RD. 10,00 mm.		Min. 315	425	600	15							
Max.												
Temperature °C 20	Spec. N° Probe Nr. Pró N°	1	579	660	697	38	41	67	207			
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co	
Min.						16,50	2,00	11,00				
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70			
	0,024	0,38	1,81	0,032	0,029	17,00	2,01	11,00	0,44	0,0225	0,16	
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektralkontrollprüfung Antimezcla			Grain Size Korngröße Tamaño de grano			
O.K.			O.K.			O.K.						
Remarks - Bemerkungen - Observaciones												
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.			
F10764 1/4" NPT Hex Plug 10K									Works Inspector Der Werkssachverständige Inspector de fábrica			