



Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SCI 6000360
ISO 14001 / SCI 1870678

ACEROS INOXIDABLES
OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY149BD-ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach **EN 10204/3.1** Certificate n° - Prüf-Nr **184144** Date - Datum - Fecha **03 - 03 - 2014**
Certificado tipo Certificado n°

Our order N° **540978** Heat Schmelze **313221** Your order N° **OL6243**
Werks - Nr Bestell - Nr
N° de Referencia Colada Pedido N°

Steel Grade **316-S-11 AV** According to **BS 970:PART 3:1991.**
Werkstoff Entsprechend
Calidad Corresponde

Shape and Size - Gegenstad **HEXAGON 22,23 mm** Tolerance - Toleranz **h 11 /DIN 176** Bundles **1** Bars **576 Kg**
Perfil y dimensión Tolerancia Buñdos Stäbe
Gewicht

Requirements - Anforderungen - Exigencias
EN 10.088-3.2005. Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC
EN 10.272-2007.
ASTM A 182 / A 182M-13.
ASTM A 479 / A 479M-13a.
ASTM A 276-13.
ASME SA 479 / SA 479M-13
SAE AMS 5653H-12.
NACE MR-0175-2003/ISO 15156-3 2009.
316S31AV-1.4404-1.4401-Type 316-Type 316L.
PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG

Melting process / Erschmelzungsart / Proceso de Fusión **E.A.F. / A.O.D.** Heat treatment / Wärmebehandlung / Tratamiento térmico **1060C 4H/Std WATER/WASSER/AGUA**

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kernschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.	Min.	325	375	550	20				
	Max.								
Temperature°C 20	Spec. N° Probe Nr. Pro N°	1	508	603	656	43	46	71	197

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,022	0,45	1,80	0,038	0,028	17,30	2,01	11,05	0,35	0,0300	0,15

Visual and dimensional inspection **O.K.** Radioactivity inspection **O.K.** Antimixing test **O.K.** Grain Size **O.K.**
Besichtigung und Ausmessung Kontrolle Radioaktivitätskontrolle Spektroskop Verwechslungspr Antimezcla Korngröße
Control visual y dimensional Control de Radioactividad

Remarks - Bemerkungen - Observaciones
IC test acc./IK prüfung nach ASTM A 262 E.02. OK
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK
F10871
1/2" NPT Hex Nipple 15K
FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL
EDV / EDP
Acc. EN 10.204
Alfredo Molina
Certification
Mng.
Works Inspector
Der Werkssachverständige
Inspector de fábrica