

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4)4 71 13 00  
Fax.34-(4) 4 53 16 36



Management System  
Approved  
CERT. Nº  
SGI 6000360

OLARRA

OLARRA U.K. LTD.  
FOREST PARK - CLEOBURY MORTIMER  
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		126219		Date - Datum - Fecha 18 - 09 - 2012																			
Our order N° Werks - Nr N° de Referencia		460027		Heat Schmelze Colada		337758		Your order N° Bestell - Nr Pedido N°				OL 4692															
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde				BS 970:PART 3:1991.											
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 25,65 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		4		Bars Stäbe Barras		174		Weight Gewicht Peso		2432 Kg									
Requirements - Anforderungen - Exigencias												EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-11a. ASTM A 479 / A 479M-11. ASTM A 276-10. ASME SA 479 / SA 479M-11a. NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653F-02. 316S31AV-1.4404-1.4401-TP.316L-TP.316. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG				Anhang I Bsatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC											
Melting process / Erschmelzungsart / Proceso de Fusión						E.A.F. / A.O.D.						Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA															
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kerschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min. 325		375		550		20																			
Temperature °C 20		Spec. N° Probe Nr. Pro N°		1		387		441		588		45		73		179											
Min.		C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co					
Max.		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70									
		0,019		0,37		1,83		0,031		0,026		17,10		2,07		11,05		0,33		0,0210		0,10					
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional				O.K.				Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad				O.K.				Antimixing test Spektroskop Verwechslungspr Antimezcla				O.K.				Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones												IC test acc./IK prüfung nach ASTM A 262 E.02. OK				<p>FLOW TECHNOLOGY LTD</p> <p>TEST CERTIFICATE</p> <p>VERIFIED TRUE</p> <p>COPY OF ORIGINAL</p>				EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.							
F10917 1/4" BSPP HEX FULL SOCKET 10K 316L																				Works Inspector Der Werkssachverständige Inspector de fábrica							