

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4)4 71 13 00
Fax.34-(4) 4 53 16 36



Management System
Approved
CERT. Nº
SGI 6000360

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 149BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		126219		Date - Datum - Fecha		18 - 09 - 2012	
Our order N° Werks - Nr N° de Referencia		460027		Heat Schmelze Colada		337758		Your order N° Bestell - Nr Pedido N°		OL 4692	
Steel Grade Werkstoff Calidad						316-S-11 AV					
According to Entsprechend Corresponde						BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 25,65 mm			Tolerance - Toleranz Tolerancia h 11 /DIN 176			Bundles Bunde 4 Bultos		Bars Stäbe 174 Barras		Weight Gewicht Peso 2432 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-11a. ASTM A 479 / A 479M-11. ASTM A 276-10. ASME SA 479 / SA 479M-11a. NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653F-02. 316S31AV-1.4404-1.4401-TP.316L-TP.316. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Bsatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.						Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 325	375	550	20						
Temperature °C 20		Spec. N°. Probe Nr. Pro N°.	1	387	441	588	45	73	179		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,019	0,37	1,83	0,031	0,026	17,10	2,07	11,05	0,33	0,0210	0,10
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektroskop Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano		
O.K.			O.K.			O.K.					
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.		
F10990 1/2" BSPP F/F SWIV STR 15K 316L									Works Inspector Der Werkssachverständige Inspector de fábrica		