


Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador

Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		219246		Date - Datum - Fecha		26 - 01 - 2015	
Our order N° Werks - Nr N° de Referencia		548620		Heat Schmelze Colada		381186		Your order N° Bestell - Nr Pedido N°		OL6407	
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión		HEXAGON 15,88 mm		Tolerance - Toleranz Tolerancia		h 11 / DIN 176		Bundles Bunde Bultos		4	
								Bars Stäbe Barras		Weight Gewicht Peso	
										2135 Kg	
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC. Annex I, Paraq.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico					
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA					
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules		
RD. 10,00 mm.		Min. 315	425	600	15						
Max.											
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	579	660	697	38	41	67	207		
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						18,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,024	0,38	1,81	0,032	0,029	17,00	2,01	11,00	0,44	0,0225	0,16
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional		O.K.		Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad		O.K.		Antimizing test Spektroskop Verwechslungspr Antimezcla		O.K.	
										Grain Size Korngröße Tamaño de grano	
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						<div style="border: 2px solid red; padding: 5px; text-align: center;"> <b>FLOW TECHNOLOGY LTD</b>  <b>TEST CERTIFICATE</b>  <b>VERIFIED TRUE</b>  <b>COPY OF ORIGINAL</b> </div>			EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng.  Wörks Inspector Der Werkssachverständige Inspector de fábrica		
F11077 1/4" NPT Hex Plug 10K											