




Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador 
Works Inspector Stamp - Werkssachverständiger
Sello del Inspector 

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		254350		Date - Datum - Fecha 09 - 12 - 2015															
Our order N° Werks - Nr N° de Referencia		584938		Heat Schmelze Colada		399014		Your order N° Bestell - Nr Pedido N°				OL6922											
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde		BS 970:PART 3:1991.									
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 34,93 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		6		Bars Stäbe Barras		132		Weight Gewicht Peso		3454 Kg					
Requirements - Anforderungen - Exigencias												Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC											
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-14. ASTM A 276-15. ASME SA 479 / SA 479M-13 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG																							
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico																	
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA																	
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																							
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																							
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA		Rp 1% N/mm2 MPA		Rm N/mm2 MPA		A %L 5D		A %L 4D		Z %		Hardness Härte HBw		Impact test / Kerschlag / Resiliencia ISO V Jules							
RD. 10,00 mm.		Min. 325		375		550		20															
		Max.																					
Temperature °C 20		Spec. N° Probe Nr. Pro N°		1		360		402		557		47		50		73		174					
		C		Si		Mn		P		S		Cr		Mo		Ni		Cu		N		Co	
Min.												18,50		2,00		11,00							
Max		0,030		1,00		2,00		0,045		0,030		18,50		2,50		14,00		0,70					
		0,029		0,42		1,62		0,035		0,027		17,25		2,04		11,05		0,39		0,0300		0,18	
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional				Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad				Antimixing test Spektroskop Verwechslungspr O.K. Antimezcla				Grain Size Korngröße Tamaño de grano											
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica											
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK												FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL											
F11419 1 5/16" JIC Swivel Female x 1/2" BSPP Cone Seat Male 10K																							