

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 149BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
 Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
 Sello del Inspector



Certificate type - APZ Nach Certificado tipo <b>EN 10204/3.1</b>		Certificate n° - Prüf-Nr Certificado n° <b>228183</b>		Date - Datum - Fecha <b>01 - 04 - 2015</b>							
Our order N° Werks - Nr N° de Referencia <b>553999</b>	Heat Schmelze Colada <b>390260</b>	Your order N° Bestell - Nr Pedido N° <b>OL6508</b>									
Steel Grade Werkstoff Calidad <b>316-S-11 AV</b>	According to Entsprechend Corresponde <b>BS 970:PART 3:1991.</b>										
Shape and Size - Gegenstand Perfil y dimensión <b>HEXAGON 22,23 mm</b>	Tolerance - Toleranz Tolerancia <b>h 11 /DIN 176</b>	Bundles Bunde Bultos <b>6</b>	Bars Stäbe Barras <b>336</b>	Weight Gewicht Peso <b>3493 Kg</b>							
Requirements - Anforderungen - Exigencias											
EN 10.088-3.2005. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 SAE AMS 5653H-12. NACE MR-0175-2003/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC								
Melting process / Erschmelzungsart / Proceso de Fusión <b>E.A.F. / A.O.D.</b>		Heat treatment / Wärmebehandlung / Tratamiento térmico <b>1060C 4H/Std WATER/WASSER/AGUA</b>									
<b>Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-</b>											
Test results - Ergebnis der Prüfungen - Resultados de los ensayos											
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas <b>RD. 10,00 mm.</b>	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschschlag / Resiliencia ISO V Jules			
Temperature°C <b>20</b>	Spec. N° Probe Nr. Pro N°.	<b>1</b>	<b>444</b>	<b>574</b>	<b>647</b>	<b>36</b>	<b>39</b>	<b>73</b>	<b>217</b>		
	<b>C</b>	<b>Si</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Cr</b>	<b>Mo</b>	<b>Ni</b>	<b>Cu</b>	<b>N</b>	<b>Co</b>
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,021	0,41	1,79	0,034	0,028	17,05	2,02	11,00	0,57	0,0260	0,20
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional <b>O.K.</b>	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad <b>O.K.</b>		Antimixing test Spektroskop Verwechslungspr Antimezcla <b>O.K.</b>		Grain Size Korngröße Tamaño de grano						
Remarks - Bemerkungen - Observaciones											
IC test acc./IK prüfung nach ASTM A 262 E.13. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK											
<div style="border: 2px solid red; padding: 5px; display: inline-block;"> <b>FLOW TECHNOLOGY LTD</b>  <b>TEST CERTIFICATE</b>  <b>VERIFIED TRUE</b>  <b>COPY OF ORIGINAL</b> </div>											
<b>F11530</b> <b>1/2" NPT RT Hex Plug 10K</b>											
<b>EDV / EDP</b> <b>Acc. EN 10.204</b> <b>Alfredo Molina</b> <b>Certification</b> <b>Mng.</b>  Works Inspector Der Werkssachverständige Inspector de fábrica											