

Larrondo LOIU (VIZCAYA) España  
P.O. Box 1.323/48080 Bilbao  
Tel. 34-(4) 4 71 13 00  
Fax.34-(4) 4 53 16 36


Management Systems  
Certified by  
LRQA  
ISO 9001 / SGI 6000360  
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

**OLARRA**

**OLARRA U.K. LTD.**  
**FOREST PARK - CLEOBURY MORTIMER**  
**NR KIDDERMINSTER - DY 14 9BD - ENGLAND**

Trade Mark - Zeichen des Lieferwerkes  
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger  
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		280778		Date - Datum - Fecha 13 - 07 - 2016									
Our order N° Werks - Nr N° de Referencia		606529		Heat Schmelze Colada		414342		Your order N° Bestell - Nr Pedido N°				OL7352					
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.					
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 27,94 mm			Tolerance - Toleranz Tolerancia h 11 /DIN 176			Bundles Bunde Bultos		4		Bars Stäbe Barras		131		Weight Gewicht Peso		2230 Kg	
Requirements - Anforderungen - Exigencias												Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 NACE MR-0175/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG																	
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico											
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA											
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																	
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																	
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kerschlag / Resiliencia								
RD. 10,00 mm.		N/mm2	N/mm2	N/mm2	%L 5D	%L 4D	%	Härte	ISO V Jules								
		MPA	MPA	MPA				HBw									
Min.		325	375	550	20												
Max.																	
Temperature °C 20		Spec. N° Probe Nr. Pro N°.	1	417	498	616	43	46	73	192							
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co						
Min.						16,50	2,00	11,00									
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70								
	0,027	0,46	1,70	0,034	0,024	17,00	2,04	11,15	0,33	0,0290	0,22						
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngröße Tamaño de grano								
O.K.			O.K.			O.K.											
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng.					
IC test acc./IK prüfung nach ASTM A 262 E.14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK												<div style="border: 2px solid red; padding: 5px; text-align: center;"> <b>FLOW TECHNOLOGY LTD</b>  TEST CERTIFICATE  VERIFIED TRUE  COPY OF ORIGINAL </div>					
F11660 1/2" BSPP Cone Seat Male x 1/4" BSPP Fixed Female Adaptor 10K																	
												Works Inspector Der Werkssachverständige Inspector de fábrica					