

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax. 34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY.14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n° 284867		Date - Datum - Fecha 16 - 09 - 2016						
Our order N° Werks - Nr 606526 N° de Referencia	Heat Schmelze 414375 Colada	Your order N° Bestell - Nr OL7352 Pedido N°								
Steel Grade Werkstoff 316-S-11 AV Calidad		According to Entsprechend BS 970:PART 3:1991. Corresponde								
Shape and Size - Gegenstand Perfil y dimensión HEXAGON 22,23 mm	Tolerance - Toleranz Tolerancia h 11 /DIN 176	Bundles Bunde 4 Bultos	Bars Stäbe 231 Barras	Weight Gewicht 2492 Kg Peso						
Requirements - Anforderungen - Exigencias										
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU			Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC							
Melting process / Erschmelzungsart / Proceso de Fusión E.A.F. / A.O.D.		Heat treatment / Wärmebehandlung / Tratamiento térmico 1060C 4H/Std WATER/WASSER/AGUA								
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-										
Test results - Ergebnis der Prüfungen - Resultados de los ensayos										
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 7D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.		Min. 325	375	550	20					
		Max.								
Temperature °C 20	Spec. N°. Probe Nr. Pro N°.	1 497	568	639	38	41	73	217		
C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.					16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70	
	0,027	0,31	1,78	0,036	0,029	17,15	2,04	11,10	0,39	0,0250 0,22
Visual and dimensional inspection Besichtigung und Ausmessung O.K. Control visual y dimensional		Radioactivity inspection Radioaktivitätskontrolle O.K. Control de Radioactividad		Antimixing test Spektrsk Verwechslungspr O.K. Antimezcla			Grain Size Korngröße Tamaño de grano			
Remarks - Bemerkungen - Observaciones										
IC test acc./IK prüfung nach ASTM A 262 E. 14. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL				EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng.
F11746 3/4" X 7/16" JIC M/M RED ADAPTOR 10K 316L										Works Inspector Der Werkssachverständige Inspector de fábrica