

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36


Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo	EN 10204/3.1	Certificate n° - Prüf-Nr Certificado n°	278465	Date - Datum - Fecha	24 - 06 - 2016
---	--------------	--	--------	----------------------	----------------

Our order N° Werks - Nr N° de Referencia	602779	Heat Schmelze Colada	411918	Your order N° Bestell - Nr Pedido N°	OL7282
--	--------	----------------------------	--------	--	--------

Steel Grade Werkstoff Calidad	316-S-11 AV	According to Entsprechend Corresponde	BS 970:PART 3:1991.
-------------------------------------	-------------	---	---------------------

Shape and Size - Gegenstand Perfil y dimensión HEXAGON 25,65 mm	Tolerance - Toleranz Tolerancia h 11 /DIN 176	Bundles Bunde Bultos	4	Bars Stäbe Barras	146	Weight Gewicht Peso	2018 Kg
---	---	----------------------------	---	-------------------------	-----	---------------------------	---------

Requirements - Anforderungen - Exigencias

EN 10.088-3.2014.
EN 10.272-2007.
ASTM A 182 / A 182M-15.
ASTM A 479 / A 479M-15.
ASTM A 276-15.
ASME SA 479 / SA 479M-15
NACE MR-0175/ISO 15156-3 2009.
SAE AMS 5653H-12.
316S31AV-1.4404-1.4401-Type 316-Type 316L.
PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG

Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC

Melting process / Erschmelzungsart / Proceso de Fusión	E.A.F. / A.O.D.	Heat treatment / Wärmebehandlung / Tratamiento térmico	1060C 4H/Std WATER/WASSER/AGUA
--	-----------------	--	--------------------------------

Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-

Test results - Ergebnis der Prüfungen - Resultados de los ensayos

Dimension of Specimen Abmessungen des Probestabes Medida de las probetas	Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kerschlag / Resiliencia ISO V Jules	
RD. 10,00 mm.	Min.	325	375	550	20				
	Max.								
Temperature °C 20	Spec. N°. Probe Nr. Pro N°.	1	414	497	612	42	45	71	187

	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.						16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70		
	0,020	0,50	1,78	0,040	0,028	17,10	2,01	11,10	0,43	0,0250	0,17

Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional	O.K.	Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad	O.K.	Antimixing test Spektroskop Verwechslungspr Antimezcla	O.K.	Grain Size Korngröße Tamaño de grano
--	------	---	------	--	------	--

Remarks - Bemerkungen - Observaciones

IC test acc./IK prüfung nach ASTM A 262 E.14. OK
Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL

F11774
3/8"BSP P X 7/8" JIC M/M ADAPTOR 10K 316L

EDV / EDP
Acc. EN 10.204
Marian Tejedo
Quality Mng.

Works Inspector
Der Werkssachverständige
Inspector de fábrica