

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		236937		Date - Datum - Fecha		16 - 06 - 2015										
Our order N° Werks - Nr N° de Referencia		548631		Heat Schmelze Colada		394213		Your order N° Bestell - Nr Pedido N°		OL6408										
Steel Grade Werkstoff Calidad				316-S-11 AV				According to Entsprechend Corresponde				BS 970:PART 3:1991.								
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 41,28 mm				Tolerance - Toleranz Tolerancia h 11 /DIN 176				Bundles Bunde Bultos		4		Bars Stäbe Barras		70		Weight Gewicht Peso		2525 Kg		
Requirements - Anforderungen - Exigencias																				
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-14a. ASTM A 479 / A 479M-14. ASTM A 276-13a. ASME SA 479 / SA 479M-13 NACE MR-0175-2003/ISO 15156-3 2009. SAE AMS 5653H-12. 316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 97/23/EC, Annex I, Parag.4.3/DGR 97/23/EG						Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC														
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico														
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA														
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-																				
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																				
Dimension of Specimen Abmessungendes Probestabes Medida de las probetas		Rp0,2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min.	325	375	550	20														
		Max.																		
Temperature °C 20	Spec. N° Probe Nr. Pro N°.	1	412	500	610	43	46	72	187											
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co									
Min.						16,50	2,00	11,00												
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70											
	0,019	0,47	1,72	0,031	0,028	16,95	2,03	11,05	0,38	0,0295	0,17									
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			O.K.			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			O.K.			Antimixing test Spektrosk Verwechslungspr Antimezcla			O.K.			Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones																				
IC test acc./IK prüfung nach ASTM A 262 E.02. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK						FLOW TECHNOLOGY LTD TEST CERTIFICATE VERIFIED TRUE COPY OF ORIGINAL						EDV / EDP Acc. EN 10.204 Alfredo Molina Certification Mng. Works Inspector Der Werkssachverständige Inspector de fábrica								
F11778 1/2" BSPP Fixed Feamble x 1/2" NPT Male Adaptor 15K																				