

Larrondo LOIU (VIZCAYA) España
P.O. Box 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax.34-(4) 4 53 16 36



ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		291612		Date - Datum - Fecha 14 - 11 - 2016		
Our order N° Werks - Nr N° de Referencia		617814		Heat Schmelze Colada		420513		Your order N° Bestell - Nr Pedido N°		
								OL7539		
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.				
Shape and Size - Gegenstad Perfil y dimensión HEXAGON 34,93 mm		Tolerance - Toleranz Tolerancia h 11 /DIN 176		Bundles Bunde Bultos		7		Bars Stäbe Barras		
								Weight Gewicht Peso		
								150		
								4000 Kg		
Requirements - Anforderungen - Exigencias										
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. NACE MR-0103-12/ISO 17945-2015. NORSOK M-630 and MDS S01.					316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC					
Melting process / Erschmelzungsart / Proceso de Fusión				Heat treatment / Wärmebehandlung / Tratamiento térmico						
E.A.F. / A.O.D.				1060C 4H/Std WATER/WASSER/AGUA						
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-										
Test results - Ergebnis der Prüfungen - Resultados de los ensayos										
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kerschlag / Resiliencia	
RD. 10,00-mm.		N/mm2	N/mm2	N/mm2	%L 5D	%L 4D	%	Härte	ISC V Jules	
		MPA	MPA	MPA				HBw		
Min.		325	375	550	20					
Max.										
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	429	520	639	40	43	72	197	
C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co
Min.					16,50	2,00	11,00			
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70	
	0,022	0,59	1,53	0,033	0,028	17,15	2,03	11,10	0,35	0,0200
										0,17
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrosk Verwechslungspr Antimezcla			Grain Size Korngrösse Tamaño de grano	
O.K.			O.K.			O.K.				
Remarks - Bemerkungen - Observaciones										
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK								EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng. Works Inspector Der Werkssachverständige Inspector de fábrica		
F11896 1/4" Medium Pressure Male x3/8" NPT Fixed Female Adaptor 15K										