

Larrondo LOIU (VIZCAYA) España
P.O. Box. 1.323/48080 Bilbao
Tel. 34-(4) 4 71 13 00
Fax. 34-(4) 4 53 16 36

Management Systems
Certified by
LRQA
ISO 9001 / SGI 6000360
ISO 14001 / SGI 1870678

ACEROS INOXIDABLES

OLARRA

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector

3

Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate n° - Prüf-Nr Certificado n°		291699		Date - Datum - Fecha		14 - 11 - 2016										
Our order N° Werks - Nr N° de Referencia		617562		Heat Schmelze Colada		420539		Your order N° Bestell - Nr Pedido N°		0L7533										
Steel Grade Werkstoff Calidad		316-S-11 AV		According to Entsprechend Corresponde		BS 970:PART 3:1991.														
Shape and Size - Gegenstand Perfil y dimensión		HEXAGON 34,93 mm		Tolerance - Toleranz Tolerancia		h 11 /DIN 176		Bundles Bunde Bultos		7										
								Bars Stäbe Barras		144										
								Weight Gewicht Peso		3791 Kg										
Requirements - Anforderungen - Exigencias																				
EN 10.088-3.2014. EN 10.272-2007. ASTM A 182 / A 182M-15. ASTM A 479 / A 479M-15. ASTM A 276-16a. ASME SA 479 / SA 479M-15 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2009. NACE MR-0103-12/ISO 17945-2015. 316S31AV-1.4404-1.4401-Type 316-Type 316L.						PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC														
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico														
E.A.F. / A.O.D.						1060C 4H/Std WATER/WASSER/AGUA														
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estrado-																				
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																				
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0.2% N/mm2 MPA	Rp 1% N/mm2 MPA	Rm N/mm2 MPA	A %L 5D	A %L 4D	Z %	Hardness Härte HBw	Impact test / Kersbschlag / Resiliencia ISO V Jules											
RD. 10,00 mm.		Min.	325	375	550	20														
		Max.																		
Temperature °C 20	Spec. N° Probe Nr. Pro N°	1	408	493	600	43	46	72	183											
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co									
Min.						16,50	2,00	11,00												
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70											
	0,023	0,63	1,60	0,032	0,026	17,20	2,02	11,00	0,36	0,0245	0,19									
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			O.K.			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			O.K.			Antimixing test Spektrosk Verwechslungspr Antimezcla			O.K.			Grain Size Korngröße Tamaño de grano		
Remarks - Bemerkungen - Observaciones																				
IC test acc./IK prüfung nach ASTM A 262 E.15. OK Crack control/Rissgeprüft acc. EN 10277-1 class 2. OK										EDV / EDP Acc. EN 10.204 Marian Tejedo Quality Mng.										
F12923 1" X 1/4" NPT HEX RED NIPPLE 10K 316L										Works Inspector Der Werkssachverständige Inspector de fábrica										