

OLARRA U.K. LTD.
FOREST PARK - CLEOBURY MORTIMER
NR KIDDERMINSTER - DY 14 9BD - ENGLAND

Trade Mark - Zeichen des Lieferwerkes
Anagrama del suministrador



Works Inspector Stamp - Werkssachverständiger
Sello del Inspector



Certificate type - APZ Nach Certificado tipo		EN 10204/3.1		Certificate nº - Prüf-Nr Certificado nº		366507		Date - Datum - Fecha 16 - 10 - 2018											
Our order Nº Werks - Nr Nº de Referencia		667602		Heat Schmelze Colada		461756		Your order Nº Bestell - Nr Pedido Nº				OL8604							
Steel Grade Werkstoff Calidad						316-S-11 AV						According to Entsprechend Corresponde				BS 970:PART 3:1991.			
Shape and Size - Gegenstad Perfil y dimensión ROUND 19,05 mm				Tolerance - Toleranz Tolerancia h 9 /DIN 671 /EN 10278				Bundles Bunde Bultos		6		Bars Stäbe Barras		Weight Gewicht Peso				3930 Kg	
Requirements - Anforderungen - Exigencias												EN 10.088-3.2014. EN 10.272-2016. ASTM A 182/A 182M-16. ASTM A 479 / A 479M-17. ASME SA 479 / SA 479M-15 ASTM A 276/A 276M-17. ASME SA 276-2015 SAE AMS 5653H-12. NACE MR-0175/ISO 15156-3 2015. NACE MR-0103/ISO 17945-2015.				316S31AV-1.4404-1.4401-Type 316-Type 316L. PED 2014/68/EU, Annex I, Parag.4.3/DGR 2014/68/EU Anhang I Absatz 4.3 Certificate/Zertifikat Nr. 348/2008/MUC			
Melting process / Erschmelzungsart / Proceso de Fusión						Heat treatment / Wärmebehandlung / Tratamiento térmico						E.A.F. / A.O.D.				1060C 4H/Std WATER/WASSER/AGUA			
Solution annealed/Abgeschreckt/Hipertemple-Cold drawn/Gezogen/Estirado-Polished/Poliert/Pulido-																			
Test results - Ergebnis der Prüfungen - Resultados de los ensayos																			
Dimension of Specimen Abmessungen des Probestabes Medida de las probetas		Rp0,2%	Rp 1%	Rm	A	A	Z	Hardness	Impact test / Kersbschlag / Resiliencia										
RD. 10,00 mm.		N/mm2 MPA	N/mm2 MPA	N/mm2 MPA	%L 5D	%L 4D	%	Härte HBw	ISO V Jules										
Min.		325	375	550	20														
Max.																			
Temperature °C 20	Spec. Nº. Probe Nr. Pro Nº.	1	472	536	621	38	41	73	202										
	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N	Co								
Min.						16,50	2,00	11,00											
Max.	0,030	1,00	2,00	0,045	0,030	18,50	2,50	14,00	0,70										
	0,014	0,62	1,56	0,032	0,028	17,11	2,02	11,07	0,50	0,0250	0,14								
Visual and dimensional inspection Besichtigung und Ausmessung Control visual y dimensional			Radioactivity inspection Radioaktivitätskontrolle Control de Radioactividad			Antimixing test Spektrsk Verwechlungspr Antimezcla			Grain Size Korngröße Tamaño de grano			5-6 ASTM E-112-13							
O.K.			O.K.			O.K.													
Remarks - Bemerkungen - Observaciones												EDV / EDP Acc. EN 10.204 Marian Tejado Quality Mng.							
IC test acc./IK prüfung nach ASTM A 262 E.15. OK No welding or weld repair. Free from mercury or radio-activity contamination. Crack control/Rissgeprüft acc. EN 10277-1 class 3. OK												Works Inspector Der Werkssachverständige Inspector de fábrica							
F15023 9/16" MEDIUM PRESSURE PLUG 20K 316L																			
We hereby certify that material described herein complies with the requirements agreed on the order.																			

FLOW TECHNOLOGY LTD
TEST CERTIFICATE
VERIFIED TRUE
COPY OF ORIGINAL